Mining Journal

Established 1835

Railway & Commercial Gazette

Vol. CCXLII No. 6190

LONDON, APRIL 9, 1954

PRICE 84

- NON-FERROUS METALS
- ORES AND MINERALS
- METALLIC RESIDUES
- METAL SCRAP
- FERRO ALLOYS

YOUR INQUIRIES ARE SOLICITED



40 YEARS OF SERVICE TO THE MINING INDUSTRY

IRON ORE

MANGANESE ORE

CHROME ORE

TUNGSTEN ORE

Philipp Brothers, Inc.

70 Pine Street, NEW YORK 5, N. Y.

Cables: PHIBRO New York, N. Y.

Substataties and affiliates the

AMSTERDAM . MONTREAL . TOKYO . BUENOS AIRES . MONTEVIDEO . LA PAZ . LIMA . CALCUTTA . BOMBAY . ISTANBUL



Stop Me and Try One

-or rather don't stop me but try one on your own.

All we could say about the D.P. pick would take more space than we have available here, so we suggest you drop us a line and we'll send you full details. If you're interested — and you will be - we can arrange actual trials in your pit, and you can see the economy of time and labour which these magnificent picks will effect in your coal production.




NEUMATIC PICKS

are supplied by

PALMER LERY

S.W.I STREET, LONDON,

Tel.: Abbey 7166 (2 lines)



CONCENTRATION OF MINERALS

by the

DAVIES model 47

MAGNETIC SEPARATOR efficiency

- Lowest

Costs!



Tungsten Tin

Noibium Titanium Base Metals


Rare Earths

DAVIES MAGNET WORKS LIMITED

WARE · HERTFORDSHIRE · TELEPHONE WARE 489

PENNSYLVANIA

SINGLE ROLL CRUSHERS



This Penn-Lehigh type, built by Fraser & Chalmers, is suitable for crushing average hard limestones, also rocks and minerals of similar hardness.

Larger sizes will crush 36" boulders to a product of 6" and under with a working capacity up to 600 tons per hour.

Other types are manufactured to handle soft rooks, minerals and coal with equal efficiency.

FRASER & CHALMERS

FRASER & CHALMERS ENGINEERING WORKS
ERITH - KENT

Tanalith PRESERVED



COVER BOARDS for LONG

> Pressure impregnation with Wolman 'Tanalith' preservative protects timber from fungal decay and wood destroying insects. The treatment makes timber last at least 10 times as long as untreated timber when installed in situations where decay is prevalent. This vastly increased, maintenance free, service life makes timber a most economical mining material. Wolman preservatives are the most widely used of any for mining work the world over.

SLEEPERS



HICKSON'S TIMBER IMPREGNATION CO. (G.B.) LTD. Export Sales Office: 36 VICTORIA STREET, LONDON, S.W.I. Cables: 'Roseine, London.'

Branches in SOUTH AFRICA, WEST AND EAST AFRICA, CENTRAL AFRICA, NEW ZEALAND, AUSTRALIA, MALAYA, TURKEY



FILTERS PROVIDE THE ANSWER

INGATE PLACE, LONDON, S.W.8


'PHONE: MACAULAY 1011

WOLVERHAMPTON DIAMOND DIE & TOOL Co. Ltd.

ROARTS INDUSTRIAL DIAMONDS **Exporters**

II HATTON GARDEN, LONDON, E.C.I.

Telephone: HOLborn 3017 Cables: Pardimon, London




'NOBEL-GLASGOW' Explosives and Accessories

There is a 'Nobel-Glasgow' explosive for every blasting operation.


Users are invited to apply to the Nobel Division of Imperial Chemical Industries Limited for assistance with their problems.

IMPERIAL CHEMICAL INDUSTRIES LIMITED NOBEL DIVISION, 25 BOTHWELL STREET, GLASGOW, C.2





BENTLEY WORKS . DONCASTER . TELEPHONE 54177-8-9



LINKS IN A WORLD-WIDE SERVICE

HOME SUBSIDIARY COMPANIES.
GEORGE COOPER & SONS.
NUIS, Bolls, Washers and Fastenings.
DARLINGTON RAILWAY PLANT & FOUNDRY CO. LTD.
SWItches and Crossings, Railway Accessories.
DICK'S ASBESTOS and HISULATING CO. LTD.
Abbeston Packings, Jointings and Insulation.
KETTON PORTLAND CEMENT CO. LTD.
Portland Cement and Ketton Freestone.
LOWMOOR BEST YORKSHIRE IRON LTD.
Wrought Iron Bars and Sections, Plates and Sheets.
HIDLAND IRON CO. LTD.
Wrought Iron and Sleel Bars and Sections, Hoops
and Sirejs.
MORTH LONSCAL'S TAR MACADAM LTD.
ROAD COnstruction Engineers and Contractors.
SHAP GRANITE CO. LTD.
Architectural and Engineering Granite. Precast
Concrete Products.
SILENT MACHINE & ENGINEERING CO.
FOOD Preparing Machinery.
JOHN SHITH (KEIGHLEY) LTD.
Overhead and Derrick Cranes. Stone Working
Machinery.
HOMAS SHITH & SONS (RODLEY) LTD.
Steam, Electric and Diesel Cranes. Universal
Excavators.
WIDES FOUNDRY & ENGINEERING CO LTD.
CASTINGS and Constructional Steebwork for the
Chemical, Oil, Food and alled industries.
JOHN WILLIAMS (WISHAWY) LTD.
Steel Plates and Sheets. Wire and Wire Products.
MOODHOUSE & MITCHELL.
Machine Tools.

OVERSEAS SUBSIDIARY COMPANIES.
THOS. W. WARD (BELGIUM) S.A.
8, Longue Rue des Claires, Antwerp.
THOS. W. WARD (INDIA) LTD.
Marshalls Buildings. Ballard Road, Bombay
and 22, Brabourne Road, Calcutta.
THOS. W. WARD (SCANDIAVIA) A/B.
Birger Jarlsgaten, 131A, Stockholm.
S.E.D.I.M.
44, Ave de la Grande Armee, PARIS XVIIE.
THOS. W. WARD (AUSTRALIA) FIT LTD.
243, Coaltereagh Street, Sydney, N.S.W.

The business founded by Thos. W. Ward in 1878 has grown from the smallest of small beginnings into a major commercial organisation with links throughout the entire industrial world.


Closely integrated with engineering and the heavier industries, the Ward Group of Companies produces many raw materials, manufactures a wide range of plant and machinery and provides at home, within the Commonwealth and throughout the world an infinite variety of general engineering products and services.

Link by link the chain has grown—purposefully, for service to industry—strengthened and annealed by 75 years' progressive experience.

THOS.W. WARD LTD

QLBION WORKS · SHEFFIELD

LONDON, GLASGOW, MANCHESTER, BIRMINGHAM, LIVERPOOL, BRISTOL, GRAYS, WISHAW, PRESTON, BARROW, BRITON FERRY, MIDDLESBROUGH, MILFORD HAVEN and INVERKEITHING.



Rover Car Factory, Solihull. High intensity lighting in a body spray tunnel by fluorescent lamps in a glazed enclosure.

Tailored for the job

The lighting of many processes is vital to the smooth and rapid flow of work and to the quality of the finished product. For example, poor lighting could make a spray tunnel into a bottle-neck — each job taking a little too long, a little portion missed, a return to the spray line — and so the whole production line marks time. Whatever form it takes, good lighting not only helps to provide a satisfactory working environment but is an active production tool.

Fluorescent lighting is as good as daylight — only more consistent. It is efficient; it is economical; and it is *flexible*. You can 'tailor' it, easily and exactly, to the special requirements of production at all stages.

Electricity for PRODUCTIVITY

HOW TO GET MORE INFORMATION

Your Electricity Board will be glad to advise you on how to use electricity to greater advantage—to save time, money, and materials. The new Electricity and Productivity series of books includes one on lighting—"Lighting in Industry". Copies can be obtained, price 9/- post free, from E.D.A., 2 Savoy Hill, London, W.C.2, or from your Area Electricity Board.

Issued by the British Electrical Development Association

The British 'Challenger' now a world contender



Hauling a 13-yard scraper this Challenger 4 is filling in the worked out Esswood open cast coal site at Essington in Staffordshire.



In clay bunkers at Surajpur, India, one man is worth a whole labour battalion when he is at the controls of the powerful Challenger 3. This British Diesel Crawler Tractor is building a great reputation for versatile efficiency right round the world. In countries new to the mechanical age the Challenger's comparative ease of operation and maintenance are proving their worth.



Five thousand feet up in Southern Rhodesia this Challenger 3 is bulldozing to prepare the ground for a new workshop extension.



Equipped with a 9-yard scraper, this Challenger 3 is moving pure white sand to form a canal near Veta Palama, 300 miles north of Madras.



A Challenger 3 fitted with hydraulically operated Bull-dozer/Angledozer is used by this gasworks in England to stack coal.

AFTER-SALES SERVICE

Wherever a machine is sold—no matter how remote the locality spares and service are readily available.

FOMMER Challenger British Diesel Crawlers

John Fowler & Co. (Leeds) Ltd., Leeds, 10.

CABLES: "FOWLER LEEDS" TELEPHONE: LEEDS 30731

PRODUCTS OF THE MARSHALL ORGANISATION

GAINSBOROUGH, ENGLAND

Concessionaires for Great Britain: Thos. W. Ward, Ltd., Albion Works, Sheffield, 4

PRACTICAL BELTMANSHIP ILLUSTRATED

CARE OF BELTS - No. 3

"Correct alignment of idlers"



THE operator of a conveyor should look at his charge with the same critical eye as the owner of a new car. When installing a new belt, for example, make sure that idlers and terminal pulleys are correctly aligned. As with a car, care when running in is essential to ensure lasting service. Correct installation followed by regular maintenance greatly increases the life of belting.

Goodyear Conveyor Belting is completely reliable. Since the early days of conveying, Goodyear have played a great part in helping forward developments and have proved the results of their extensive research in actual practice. A vast variety of installations all over the world, fitted with Goodyear Belts, have been in operation for many years. Skilled Goodyear technicians supervise manufacture from start to finish, making absolutely certain that every product upholds the Goodyear tradition of dependability.

You can find out all you want to know about the care of industrial rubber products in the Goodyear Maintenance Manual, issued free. By choosing Goodyear industrial rubber products and by following the advice in this manual you will be sure of getting maximum life from your equipment. Please write to Dep. D3, Goodyear Tyre & Rubber Co. (G.B.) Ltd., Wolverhampton.



Goodyear Style HRS

Specially made for conveying hot, highly abrasive materials when the combination of resistance to high temperatures, extreme abrasion and severe flexing are essential. Capable of handling moderately abrasive materials at temperatures up to 250°F, throughout a long and economical life.

GOODFYEAR

INDUSTRIAL RUBBER PRODUCTS

TRANSMISSION BELTING . V-BELTS . CONVEYOR BELTING . INDUSTRIAL HOSE

The Mining Journal Established 1835

Vol. CCXLII No. 6190

LONDON, APRIL 9, 1954

PRICE 8d

CONTENTS Notes and Comments 413 The Mining Markets 424 From Our Australian Correspondent Company News and Views ... 425 Continuous Electric Smelting of Low Grade Nickel Ores 415 **Company Meetings and Announcements** 426 Manganese in Southern Bombay State, India ... Orientated Diamond Drill Bits—II ... 417 The Anglo-French Exploration Company Limited; 418 Machinery and Equipment ... Metals, Minerals and Alloys 420 Anglo American Corporation of South Africa Limited; Central Mining-Rand Mines Group

Published by The Mining Journal Ltd., at 15 Wilson Street, Moorgate, London, E.C.2.

MONarch 2567

Subscription £2 per annum

NOTES AND COMMENTS

Keeping on Course

Politically, it is easy in a Budget to cut taxation, it is only slightly more difficult to increase it; but it is extremely hard to get away with leaving things alone. Circumstances have compelled Mr. Butler to try.

On the basis of present taxation an ordinary surplus of £14,000,000 could be envisaged compared with an estimated surplus last year of £109,000,000 and a realized surplus of £94,000,000. Judged against these figures the cut in taxation of £4,000,000, which has been condemned widely as niggardly, seems almost generous. It is true that the crushing weight of public expenditure had left Mr. Butler little room to manoeuvre; but his immobility was not wholly forced upon him; it was willingly assumed for two reasons. First, the effects of 1953's Budget have not yet been worked out, and secondly the cost of its concessions have not yet been fully paid for.

If one may follow Mr. Butler-though without his attitude-in a fluvial simile, the undercurrents of the economy are not less fluid because he has refrained from doing more than dabble the surface with his oar. The dabbling that he has managed to do is exceedingly important, especially for manufacturing industry. The old initial allowance scheme gave industry nothing but the benefit of an interestfree loan, for the initial allowance was an immediate deduction from the total allowance which would have come in due course. The new investment allowance is a full allowance against tax-at the same percentage rate-which will not have to be paid for in future years. In effect, this will cost the Chancellor virtually nothing in the first year (since it operates at the same rate as the initial allowances) and only £4,000,000 in the second year, but its net additional cost to the Exchequer will build up over the years to a sum equalling the tax on 20 per cent (assuming the rate remains unchanged) of gross national fixed capital formation. The incentive effect is likely to be much less for the mining industry which already enjoys an initial allowance rate of 40 per cent. Mr. Butler believed that mine works would still find the new 20 per cent investment allowance more favourable in the long run than the old 40 per cent initial allowance but undertakings are to be allowed to choose for themselves. Further details, and particularly safeguards against abuse, are to be made known in the Finance Bill and until then final judgment-at least for the mining industry-had better be reserved.

Owners of private businesses will be glad to hear that

they are to enjoy the same relief of 45 per cent now enjoyed by agricultural land on their holdings of buildings, plant and equipment. There is no doubt of the hardship suffered by small businesses but there is nevertheless the same sort of objection to this proposal as to that of granting tax-free increases to judges and Members of Parliament—and for the same reasons.

Other Budget proposals seem matter for argument rather than of substance. But that is not all there was to Mr. Butler's speech. Twice he referred to the drastic measures which he would not shrink from taking if circumstances demanded them and this has been commonly assumed to imply the possibility of an autumn Budget. That may well be so. But it should not be forgotten that the interest rate structure has been trimmed to make possible rapid adjustment of Bank rate if it is needed. Since interest rates are now well above those of New York the Bank rate board will be watched with even greater care on Thursdays. Two dangers are no doubt in Mr. Butler's mind. The first is the future trend of the American economy. Between July, 1953, and March, 1954, production had fallen by 10 per cent; by January, 1954, the percentage fall had been equal to that of the entire 1948-49 recession which caused the devaluation of sterling. It is not merely the danger of a major slump in the United States which threatens, there is the more insidious danger of taking the wrong step to counteract the present moderate recession which to date-surprisingly-has had no serious effect on the United Kingdom's economy.

The second danger lies in the inability of European countries to agree on the control of improper government subvention to exporting industries. A new "standstill" agreement was made last week to cover the next three months; but it is known that certain European countries are chafing—in the absence of agreement—to increase financial help to exporters while the German rebate system is calculated to offer up to 4 per cent of a firm's export turnover. Assistance of this kind will become more telling as the war in export markets is fought out increasingly on price and Mr. Butler will no doubt be pressed to offer similar inducements of a kind which all British Governments have so far refused.

These seem to be powerful reasons for Mr. Butler to allow his ship to keep her present prosperous course providing his eye is well peeled to discern the storms that threaten to rock it.

America-Readjustment or Slump?

With the first quarter of the year ended without U.S. trade and industry showing any recovery, discussion on what the future holds seems to be growing and the advent of the period of major wage negotiations is being watched for any indications of how managements and the labour unions will adapt themselves to the situation.

The present slackening off in business seems to have become first apparent after the middle of last year when the active Korean War terminated. Such a transition to a more peaceful outlook naturally reduced the tempo of business just as the advent of the "emergency" had stimulated it. Some reduction in business activity, especially when compared to the corresponding months of last year, is only normal, and due allowance must be made for readjustment from a cold war to a peace economy.

The well-known magazine Fortune, after discussing the pros and cons, concludes that this "recession" year will turn out to be the second best in the nation's history. Such a reassuring conclusion, however, is far from being universal. The Wall Street Journal of April 1 says "optimism relies heavily on hope. Current barometers suggest caution."

One reason for this hesitation is no doubt the increase in unemployment, which again rose though to a much less extent in the month ended the middle of March. The number of unemployed rose to 3,725,000, the highest since March, 1950, and the total is expected to exceed 4,000,000 by July, and possibly even earlier

Hearings on the revision of the Taft-Hartley Act in the House of Representatives continue with indications that the Labour committee are not disposed towards the moderation which the President so clearly desires. Meanwhile, the Longshoremen's strike in New York, which has disorganized many trades over a considerable portion of the country, came to an end last week after the intimation that the independent international Longshoreman's Association might be struck off the ballot, when the new bargaining elections take place.

On April 1 President Eisenhower signed the Excise Tax Bill, representing a cut of \$7,400,000,000—the greatest tax cut in any single year in U.S. history. Hitherto the Administration has opposed excise cuts but considerations connected with politics seem to have converted the President and his advisers, and the measure is now blessed with their belief that the tax cut will stimulate the economy. Other measures of a minimum anti-recession programme are now being put forward.

Western mining industry leaders, while expressing appreciation of the recent second round of Government stockpiling, seem as determined as ever to push through their programme of bolstering their products by higher tariff awards.

While this question of whether we are witnessing a "readjustment" or "recession" or "slump" is perplexing industrial financial and public opinion in the U.S., it is also being watched with much anxiety abroad, and Mr. Butler in his Budget Speech on Tuesday attributed the cautious policy which he presented to the country largely to the uncertainty of how the American situation may develop.

India's First Uranium Plant

The uranium-thorium plant at Trombay is likely to go into production by the end of this year, according to a correspondent from Jamshedpur, India. This plant, he states, will process the residual cake left over from monazite after its rare earth and phosphate content have been extracted in the Alwaye factory.

This residue contains both thorium and uranium. Some

of the thorium will be turned into nitrate for the use of the indigenous gas mantle industry, but the remainder will be retained by the Atomic Energy Commission for its own use. Thorium is now regarded as the best element for use in a breeder reactor which transforms it into Uranium 233.

The uranium remaining will be extracted and purified for use in a reactor. India hopes to possess a reactor in about two years.

The Atomic Energy Commission is also setting up a plant to process uranium to a state of atomic purity.

Australia

(From Our Own Correspondent)

Melbourne, March 30.

Drilling operations carried out by West Australian Petroleum Ltd. at Rough Range, Exmouth Gulf, have been retarded by the hardness of the rock formations encountered, but sinking has now reached a depth of approximately 7,600 ft. While no further significant discoveries have been reported, the company plans to step up its exploration activities and will spend £A2,735,000 during the current year for this purpose.

A good idea of the company's intentions is, perhaps, provided by its recent purchase of a National 130 drilling plant, similar to the one in use at Rough Range, from the Commonwealth Government for £A375,000 which will be used in the Fitzroy Basin, inland from Derby, 700 miles north of Exmouth Gulf. The company's accelerated drilling programme envisages the drilling of 11 new wells in the North-West Basin during 1954. Orders for some, or all, of the equipment have been placed and two new drilling rigs will arrive from the U.S.A. during the next few weeks. One of the drill rigs will be employed at Rough Range to drill six test wells to a depth of approximately 3,600 ft., while the second drill rig will be used to put down three exploratory holes on known structures in the area south of Exmouth Gulf, between Rough Range and Carnarvon. The deep test well, designated Rough Range No. 1, which as aforementioned has been sunk to a depth of approximately 7,600 ft., will be continued, and when it has been sunk to its final depth the plant will be removed to drill an exploratory hole in the Cape Range structure to the west of Rough Range.

URANIUM AND THE GOLD MINING COMPANIES

There has been a great deal of uranium prospecting carried out by mining companies in recent months. In addition to the work already carried out by Uranium Mines N.L. (a private venture formed specifically to prospect for uranium), and Norseman Gold Mines N.L., whose discoveries in the Lake Dundas area were referred to in The Mining Journal, February 26 and March 19, there has been activity reported at Mt. Isa, North Queensland, where leases have been pegged and reports refer to intense radioactivity from samples taken from certain areas. The centre of activity is 25 miles north-west of Mt. Isa mines and the Mt. Isa Mines Ltd. has advised that it has pegged certain leases near Mt. Isa where it is believed uranium occurs.

Western Mining Corporation has also entered the uranium picture and has secured areas near Lalla Rookh, in the Marble Bar district, Western Australia. So far nothing of value has been discovered but prospecting is being carried out in other parts of the State. Western Mining Corporation and Gold Mines of Australia have come to an agreement whereby participation in all uranium activities shall be for the joint account of the two companies; the participation being in the ratio of 75 per cent to Western Mining Corporation and 25 per cent to Gold Mines of Australia.

ELECTRIC NICKEL SMELTING-I

Continuous Electric Smelting of Low Grade Nickel Ores

Although it stands as the largest consumer of nickel in the world, the United States produces virtually no nickel from domestic ores, and dependence upon outside sources and the increasing importance of nickel have focused attention of those deposits existing within the national boundaries. Research on the Cle Elum and Riddle ores from the U.S. deposits, as well as on certain ores from foreign sources, was begun nearly ten years ago and has continued ever since. In the following article, the first of two instalments, condensed from U.S. Bureau of Mines Report of investigations 5201, the structures of the ores tested are described together with the preliminary tests and electric smelting procedures, while in a further article the results of electric smelting and upgrading experiments by means of continuous selected reduction tests will be discussed.

The electric-smelting equipment comprises two furnaces designed and built at the Albany Station, except for the water-cooled electrode clamp-arm assemblies. Both furnaces are three-phase, round, open-top, with cable-suspended electrodes placed at the corners of an equilateral triangle. Provision was made for ready change of the electrode spacing. The two furnaces are backed by a common 1,000 kVA. Westinghouse transformer, the secondary busses of which may be connected in parallel or series. The transformer has six voltage taps, the series connection voltages being approximately twice those of the parallel connection. Both furnaces operate from a common operator's panel, electrode winches, and balanced-beamtype regulator panel.

The smaller furnace, designated ESA, is nominally rated at 100 kW. but has been operated at over 300 kW. with the transformer on series connection. This furnace was used in the continuous nickel-smelting tests. It employs 3 in. graphite electrodes, which generally were spaced with their centres 5½ in. from the furnace centre. The furnace has three tap holes at different levels, the lowest of which is intended to drain the hearth.

TEST FURNACES

For the smelting tests in the roofed furnace, two different designs were used. First, a ring 12 in. high with three lateral feeding chutes was placed on top of the furnace. The ring was first lined with silica brick, and the feeding chutes were lined with plastic monofirebrick. Later, the ring was lined with magnesite brick and the feeding chutes were rammed with periclase. In this furnace a large section of the electrodes was in the furnace, causing a high consumption of electrodes.

The larger furnace, designated ESB, employs 8 in graphite electrodes and operates at 500 to 1,000 kW. The shell measures 96 in. in diameter and 78 in. in height. The top part is not removable. All other characteristics are the same as for the ESA furnace. Besides the described ESA and ESB furnaces, which are essentially smelting furnaces, other electric furnaces are available at the Albany Station, in which the first smelting tests were performed.

The size ST Lectromelt, Heroult-type, steel-melting arc furnace rated at 500 kW. was converted for use as an opentop smelting furnace in early smelting tests. The charging door was bricked up, and the roof was replaced by a spare roof ring, which was lined with refractory to increase the height of the furnace wall. After the ESA furnace was brought into operation the ST furnace was changed to its original design and used for refining tests. A single-phase arc smelting furnace of 200 lb. capacity and rated at 200 kW. with manual electrode control was used for exploratory batch tests. A single-phase size W furnace of 50 lb. capacity also is available for tests where applicable.

RAW MATERIALS

The Cle Elum deposit, about 60 miles east of Seattle and 26 miles north of Cle Elum, has been investigated, disclosing several million tons of measured and indicated ore

averaging, in per cent: Fe, 42.7; Ni, .92; and Cr, 1.73. About 70 per cent of this tonnage has an average nickel content of 1.05 per cent, and the balance averages .62 per cent.

Petrographic examination of the ore revealed that the Cle Elum ore is a nickeliferous iron ore, which contains essentially magnetite, some haematite, chrome spinel, clay minerals, talc, diaspore, and minor amounts of quartz, plagioclase, chlorite, limonite, calcite, serpentine, carbonaceous matter, clinozoisite, amphibole (including glaucophane), and epidote. No discreet nickel minerals were observed. Spectroscopic examinations of concentrates indicate that essentially all of the nickel present is atomically combined with the magnetite, although minor amounts are evidently present in the serpentine and talc.

The Riddle nickel ore deposit is in south-western Oregon, and contains about 20,000,000 tons of indicated and inferred ore averaging 1.5 per cent nickel. Petrographic examination of the ore revealed the principle minerals to be limonite, antigorite, garnierite, chlorite, magnetite, talc, and pyrophyllite. Garnierite, a hydrous nickel-magnesium silicate, is the nickel mineral.

The Brazilian nickel ore from the Tocantins deposit, of which a 6 ton lot was received for smelting tests, is a garnierite-type ore similar to the Riddle ore, except for its copper and higher nickel content. The received sample analyzed, in per cent: Ni, 4.4; Fe, 12.1; Cr, 1.1; Co, .03; Cu, .42; Al₂O₃, 5.6; SiO₂, 45.6; CaO, 3.5; MgO, 10.9; S, .02; and P, .09. This ore was received crushed to minus 4 mesh.

Two samples of Cuban laterite and serpentine received and analyzed indicate that the Cuban laterite is similar to the Cle Elum ore, whereas the Cuban serpentine is more nearly similar to the Riddle ore, although its Fe content is appreciably higher.

FLUXES AND REDUCTANTS

Limestone and quartz used as fluxes were obtained from local sources and were of average commercial grade. Coos Bay coal was obtained and the char was produced by devolatilizing the coal in the rotary kiln. Roslyn coal was obtained from a mine in the vicinity of Cle Elum. Gasco briquettes consisted of petroleum carbon, and petroleum coke was of average grade and gave results comparable to those obtained using Gasco briquettes. The aluminium-ferrosilicon alloy (Al-Fe-Si), used as a possible slag scavenger, was minus 65 mesh.

	Fe	Al	Si	F.C.	CaO	MgO	SiO 2	11,0,
Limestone					52.0	0.8	3.2	1.9
Quartz							96.0	
Coos Bay coal				44.6				
Coos Bay char				68.9				
Roslyn coal	0.88			46.3	1.03	.34	7.5	6.2
Gasco briquettes				98.7				
Petroleum coke				95.3				
Al-Fe-Si	30.1	12.2	55.6					
Hogged wood								
waste*				12.6				
	*	Avera	ge an	nalyse	S			

Sawdust used as reductant and for smelting control was obtained locally and was the same as that used for industrial and home heating. Hogged fuel, a mixture of chips, splinters and sawdust, later proved superior to sawdust.

Previous research on Cle Elum ore indicated the need for departure from normal electric-smelting practice. The first test on continuous smelting of Cle Elum ore in the ESA furnace was made in April, 1952. More tests were made in October, November and December, 1952, and January, 1953. All these tests were based upon experience gained in smelting Riddle ore by the dry-top technique, using hogged fuel as reductant, and were considered of exploratory nature to determine optimum conditions.

Before smelting research on Riddle ore was undertaken several nickel-extraction methods were tried with no apparent success. Subsequent electric-smelting research was done. Seventeen batch-smelting tests were made in the single-phase, 200 lb. arc furnace, employing magnesite, silica, and carbon hearths. After two single-shift continuous smelting tests in the modified ST Lectromelt furnace, batch testing of variables in smelting of Riddle ore was concluded with 13 tests in the 200 lb. arc furnace. Additional refining on crude Riddle metal included tests on the Perrin practice, employing lime-chromite slag, refining with oxygen, and refining with iron ore. All three methods showed promise but required further testing.

In April, 1951, the new 100 to 300 kW. three-phase, opentop smelting furnace was brought into operation and employed in smelting research of Riddle ore. Numerous continuous smelting tests were made in the magnesite-lined furnace with varying amounts of Coos Bay char as reductant. Limestone was used as flux in proportions of 30, 15, and 0 parts per 100 parts of ore. In the first 19 tests slagresistance smelting technique was used; in other words, the electrode tips were immersed in the slag. Two slagresistance heats were made in the carbon-lined furnace followed by four heats using arc resistance with the electrode tips above the slag. Finally, in the series of preliminary tests, one arc-resistance heat was made on a magnesite lining.

RESULTS OF THE TESTS

Results of the preliminary tests indicate that low-carbon and low-silicon ferronickel was produced only from a carbon-deficient charge in magnesite-lined furnace by arc resistance smelting. Charges with a small excess of carbon produced a ferronickel with a high carbon and low silicon content. A high silicon, low-carbon ferronickel was produced from charges containing a large excess of carbon. Results of the tests show that a relationship exists between the silicon and the carbon contents of the alloy. With higher silicon content, the carbon content is lower, which leads to the conclusion that carbon is replaced by silicon.

Boiling and foaming conditions experienced in heats with carbon deficiency in the charges, made in carbon-lined furnace or using slag-resistance smelting technique, is believed to be caused by the reaction of the carbon from the lining or the electrodes with the oxides in the slag.

SMELTING PROCEDURES

The general procedures in handling ore, reductant and fluxes, slag and alloys were similar in all tests made in the ESA furnace. Portions of ore ranging from 100 to 300 lb. were weighed and mixed with the weighed amount of reductant and fluxes. Brazilian ore and Riddle ore were mixed with reductant in a large concrete mixer, but the Cle Elum ore charges were mixed by shovel on a concrete pad.

Several different materials were tried for botting up the tapholes. A mixture of crushed magnesite brick and peri-

clase or straight periclase proved to be the best. Slag was sampled by dipping a slag spoon into the molten slag and pouring the spoon's content on to a clean graphite plate. Analytical results showed very good correspondence. During the Riddle and Brazilian ore tests the alloy was tapped into a 29 in. diameter geared ladle, which was lined with 4 in. of plastic firebrick. The slag tapped with the alloy was skimmed off, and then the remaining slag and alloy were pigged in 15 lb. cast iron pig moulds. The alloy samples were drilled from the middle pig.

Owing to the relatively larger amount of slag and a smaller alloy yield from the Cle Elum ore, taps were made more frequently and the alloy was tapped with the slag. The alloy collected in the lower part of the mould, whereas the slag remained on top. After freezing, separation was good and the alloy regulus was easily separated from the slag. Slag samples continued to be taken the same way. Whenever possible, a molten alloy sample was taken by dipping the spoon sample deep into the mould and pouring its content into an iron mould.

SMELTING INVESTIGATIONS

Three general types of smelting were investigated, drytop, open-arc, and smelting in a roofed furnace. The drytop technique was applied when smelting Brazilian nickel ore. During the tests on Riddle ore, dry-top smelting used in the beginning was later replaced by open-arc smelting. Most of the tests on Cle Elum ore were made under dry-top conditions. Only part of the last series of smelting tests was made in a roofed furnace.

Experience proved that low-grade nickel ores can be selectively smelted by the dry-top smelting method. However, certain requirements of the charges are indispensable to secure success. Hogged fuel proved to be of great value for dry-top smelting. The hogged fuel mixed with the ore and the flux not only provides the carbon necessary to reduce the ore but maintains a porous, non-conducting, insulating cover over the molten bath. The porous nature of the cover allows the gases formed by the reaction of the oxides with the carbon to escape constantly, preventing accumulation of gases in the furnace, which eventually causes violent blows, with consequent loss of dust and metal vapours.

Hogged fuel, being a poor conductor of electricity, prevents current from flowing from one electrode to the other through the charge; this can result in inoperable furnace conditions. The current must flow between the electrode tips and the molten bath. On the other hand, hogged fuel, being a good insulator of heat, reduces heat losses when covering the molten bath. Increasing the amount of hogged fuel in the charge decreases the feeding rate of the ore into the smelting zone and raises the smelting temperature. In selective-reduction smelting the amount of hogged fuel is limited by the carbon requirement. Smelting in a roof-covered furnace established that selective reduction of Cle Elum or other similar ore using coke or coal as reductant without hogged fuel was also practical.

A 4 in. to 6 in. layer of ore and flux was placed on the hearth as a cushion, and the corresponding amount of crushed Gasco briquettes was placed on top of the ore-flux mixture. The roof was then placed on top of the furnace and the electrodes introduced into the furnace through the electrode clamps and holes in the roof. After a molten pool was established by arcing the crushed briquettes, the charges were added to the furnace through the feeding chutes.

The general procedure was to keep the electric arcs short and feed the charges to the furnace at a rate that kept the bath always covered with some unfused charge, thus protecting the sidewalls and the roof from direct arc radiation.

Manganese in Southern Bombay State, India

The first portion of this article, which appeared in our last issue, outlined the activities of those manganese mining companies active in the northern section of Bombay State, India. In the concluding instalment, which appears below, the activities of those companies operating in the southern part of the State are described.

The Independent Trading Co., which holds a mining concession comprising 2,000 acres in the Talevadi area of Belgaum, is an affiliate of the Eastern Mining Co. and has begun working a mine in the area, 21 miles from Londa. Operations began in October, 1952, and an output of 2,000 tons monthly was expected by the end of 1953. The ore is a compact type and, having the same characteristics as the Joida ore, is described as "disintegrated reef deposits." Fifty per cent of the ore produced is medium-grade, 30 per cent high-grade, and 20 per cent low-grade. At present 200 workers on a contract basis are employed.

The Shri Ram Mining Co. obtained a prospecting licence for the Jamgaon mine, 18 miles from Londa, in April, 1952. The lease covers 6 deposits in an area of 640 acres. Deposits are mostly on the surface and in the immediate subsoil and are described by the lessee as "pocket ore in boulders and gravels." Without serious prospecting, the company estimates its reserves at 60,000 tons comprising 30 per cent high-, 30 per cent medium-, and 40 per cent low-grade ore. Monthly production is 400 tons with a labour force of 150.

NORTH KANARA

The most recent geological survey of manganese deposits in the North Kanara district was made by K. C. Channabasappa, of the Geological Survey of India, who estimated reserves of manganese ore to constitute 500,000 l.tons of all grades.

The Eastern Mining Co. operates four mines in south Bombay State, the Titwali, 13 miles from Londa, Kurandi, 13 miles from Londa, Usoda, 22 miles from Londa, and Pardhani, 37 miles from Londa.

The Titwali mine consists of four deposits of which two are being worked, and which consist of pocket ore floating in irregular directions. In some places there are outcrops, but in other places the ore pockets are 15 to 20 ft. underground. Mining is with pick axes and crow bars, and the ore is separated from waste dirt, broken into small pieces, and graded. A monthly production of 1,000 tons of ore is extracted by 60 workers using no equipment. Mining is confined to eight months of the year and the mine is flooded during the rainy season.

The Kurandi mine was previously prospected by Killick Nixon and Co. and then abandoned. The main deposit in this 80 acre concession shows evidence of reef formation consisting of high-grade ore and also pyrolusite of 94 per cent purity. The mine is open-pit and worked by blasting and hand tools. Considerable development is being undertaken to expose the orebody. Production in 1953 was expected to be 6,000 tons for the eight months of production. The four deposits are worked by 70 workers, and monthly production averages 600 tons. If the reef deposits are traced to any significant extent, the company plant modern mechanization of the mine.

The Usoda mine consists of seven deposits in an area of 460 acres, the character of the deposits being the same as in Titwali. Iron ore also is found in the mine but is not worked owing to the uneconomic costs of production. The mine, employing 160 workers on a contract basis, produces 7,000 tons of ore annually. Larger production is hampered by the Government Forest Department's reluctance to grant permission to clear the forest area for mining. All three

grades of ore are produced, 30 per cent high-grade, 30 per cent medium-grade, and 40 per cent low-grade.

The Pardhani mine consists of four deposits in an area of 840 acres in which pocket and boulder deposits are found. Prospecting by digging trenches is under way in the area to determine the scope for mechanization. At present 200 workers, employed on a contract basis, produce 1,000 tons of ore monthly by opencast methods using simple hand tools. In 1953, production was expected to be 10,000 tons for the eight working months. The ore is about 60 per cent medium-grade, 30 per cent low-grade, and 10 per cent high-grade. The phosphorus and silica contents are low and the ore, though predominantly medium-grade, is blended with ores from other areas.

OTHER OPERATORS

Bapusaheb Tilve and Sons operate the Shiroli and Castle Rock deposits, 38 and 18 miles respectively from Londa. Both consist of opencast pocket deposits operated by hand, utilizing a few hand tools. Work at the Shiroli deposit has progressed to about 60 ft. below ground level, but mining at Castle Rock is a surface operation. Annual production at Shiroli is 5,000 tons and Castle Rock 3,000 tons, extracted during the eight months of clement weather. The ores are high-grade with about 30 per cent medium- and 30 per cent low-grade.

Near the end of 1952 Shamalsha Girdhari and Co. secured a prospecting lease for the Khodli mine comprising 400 acres containing deposits in pockets. Mining was scheduled to begin in April, 1953, and production for the year was placed at 2,000 tons. The ore is 40 per cent high-grade, 40 per cent medium-grade, and 20 per cent low-grade, 40 per cent medium-grade, and 20 per cent low.

B. H. Mehta Co. have obtained a prospecting lease to operate mines in four areas, Ivoli Ghotagi, Khodli, Vilya, and Kalumbuli in North Kanara district. The Ivoli Ghotagi mine is the only one operating, but the other three are expected to be opened shortly. The Ivoli Ghotagi lease covers 400 acres in which pocket deposits containing all grades of ore (40 per cent high-grade, 30 per cent medium-, and 30 per cent low-grade) are found. Present monthly production is 250 tons, with a labour force of 60. A total of 2,500 tons was expected from the four mines in 1953.

OPERATIONS IN JOIDA

Lalbhai Patel Co. has mining leases for a group of four mines in Joida, 26 miles from Londa. Of these only one is being worked, although the other three are expected to begin operations in 1954. The Joida mine area comprises 1,100 acres 2,000 to 3,000 ft. above sea level, and the deposits are described as "disintegrated reef." In several places the orebody appears as an outcrop and in others there is evidence of the orebody dipping several feet below the surface. Mining is open pit and compressors, drills, bulldozers, and hand tools are used. The ore requires considerable dressing before grading, which is done by rotating pieces of ore in a steel drum inset with sharp spikes on its inside surfaces. Considerable prospecting and development is being undertaken by the company, and as a result of sinking trial pits and drill shafts, ore reserves are estimated at 1,000,000 to 1,500,000 tons. The mine is producing 5,000 tons of ore monthly with a labour force of 800.

Orientated Diamond Drill Bits-II

In last week's issue, the first portion of this article discussed tests carried out by the United States Bureau of Mines in the orientation of diamond drill bits. In the final instalment appearing below, tests carried out by certain companies in the United States are described as well as investigations on cube shaped diamonds.

While the research work discussed in the first part of this article was based on experiments conducted under closely controlled conditions, another publication (A. E. Ross, A. E. Long, 1953) gives the practical experience of Sprague and Henwood Inc. It clearly indicates that setting in hard-vector directions is feasible and reduces drilling costs. In these tests 4,000 powder metal orientated bits were set and used, and the report gives results covering a portion of these. The procedures used in orientating the diamonds were based on methods by A. E. Long and C. B. Slawson (1952).

A few orientated bits were tested under field conditions in 1950. Five pairs of diamond coring bits were made, identical as to diamond quality, size, carat weight, bit type, matrix, crown contour and waterways. Diamonds were orientated in hard-vector directions in one bit of each pair and set at random in the other. Each orientated bit drilled 27.4 ft. costing \$.595 per ft. drilled with .055 ct. diamond loss. Random set bits drilled 9.2 ft. each, at \$1.460 bit cost and .133 ct. loss per ft.

First Test Bits

			Random-set	Orientated
No. of bits tested			 5	5
Total ft. drilled			 46	137
Ft. drilled per bit			 9.2	27-4
Total diamond loss			 6.10	7.59
Diamond loss per	ft. dri	lled, ct.	 0.133	0.055
Bit cost per ft. dril			 \$1.460*	\$0.595*

[•] Includes cost of diamonds consumed, resetting, and blanks.

Additional personnel had to be trained to produce sufficient orientated diamond bits for field tests on a wide cross section of rock types and drilling conditions. A new series of test bits, paired as before, was sent out in 17 groups, consisting of 6 to 12 pairs per shipment. Different diamond types and grades were used, but the majority were medium grade boart, 10 to 15 stones per ct.

TESTS IN HARD ROCK

Solid and broken formations were drilled, ranging from shales to granitic gneiss, and some bits subjected to abuses, e.g. drilling over broken core and tramp iron. All 272 bits were salvaged by January, 1953.

Second Test Bits

			Random-set	Orientated
No. of bits tested		.,	129	143
Total ft. drilled			2773	4381
Ft. drilled per bit			21.5	30.6
Total diamond loss, ct.			354 - 53	338.08
Diamond loss per ft. drill	ed, ct.		0.012	0.008
Bit cost per ft. drilled			\$1.05	\$0.66*

^{*} Does not include charge for extra time required to orientate diamonds in setting.

Average figures showed that orientated bits drilled 30.6 ft. each, cost per ft. drilled being \$.66 with .008 ct. loss. Random set bits drilled 21.5 ft. each at \$1.05 bit cost per ft. drilled and .012 ct. loss.

Several difficulties prevent full use being made of the better performance of orientated bits. Orientation requires skill, a long training period and consequent high wages, in addition to taking longer than random setting. So far, bit orientation has been largely confined to diamonds larger than 20 per ct., though smaller stones are preferred in many drilling operations. With further experience the range of suitable sizes may be extended to diamonds as small as 40 per ct. Within the present size limitation, a large proportion—though not all—of new diamonds can generally be orientated, though this is reduced when diamond shapes are altered by wear or surface features obscured by a dark coating. Suitable stones, therefore, are likely to become costly.

Only if the problems connected with bit orientation are solved can the average diamond user hope to purchase orientated bits at a reasonable price.

BIT PERFORMANCE IN COAL FORMATIONS

Officials of Hoffman Bros. Drilling Co., also following the report of A. E. Long and C. B. Slawson (1952), experimented with the orientation of diamonds in bits, and since January, 1953, only bits with diamonds orientated in the hard-vector direction are being manufactured. The following table presents data for NX bits with beryllium-nickel matrices, cast-set with medium grade diamonds of 6 to 10 per ct. size. The drilling was done in coal formations, i.e. in sedimentary rocks for which large-stone bits were most suitable. Additional setting charges become necessary, of course, increasing in inverse ratio to the size of the stones, but the report claims that these are greatly offset by savings.

Summary of results for NX bits

		Random-set*	Orientated*
No. of bits tested	 	46	40 -
Total ft. drilled	 	7340	7693
Total diamond loss, ct.	 	118 · 78	65 · 58
Diamond loss per ft., ct.	 	0.01618	0.00852
Diamond loss per bit, ct.	 	2.58	1.64
Average footage per bit	 	159.6	192 - 3

^{*} In sedimentary rock, broken limestone and in strip-drilling coal.

E. P. Pfleider investigated octahedron shape diamonds set in various directions (1952) but continued these investigations with cube-shaped diamonds. Seven bits were set with cube-shape diamonds about 10 stones per ct. in size, the stones being of nearly perfect cubic form and easily orientated. Five orientations were tested, using the Hy Mac hydraulic drill unit, EXT diamond core bits and drilling St. Cloud pink granite.

CUBE FACE DIAMONDS

Bits M-11 and M-15 tested a positive rake off the cube face, with the cube corner or point leading. This orientation gives a cutting force of diamond on rock more ore less normal to the octahedral cleavage, and is preferred for octahedral diamonds. But with cube diamonds the points wore down rapidly and tended to form polished flats, with a resulting decrease in penetration rate. On reaching a critical pressure, one or more of the diamond points failed, destroying some of the gauge diamonds. The result was a high, but short-lived advance rate between 13 to 15 ft. for M-11 and 8 to 10 ft. for M-15. Footages were 18.7 and 15.3, and the overall advance rate the same.

Bit M-14 was set with diamonds having a point orientation and the cube corner trailing, and therefore a positive rake off the octahedral cleavage plane. The corners of the stones started to cleave off in the first ft. of break-in drilling, in accordance with previous experience with similar orientation of octahedron diamonds. The trailing edge tended to cleave away, followed by the formation of polished flats ahead of the broken edge and a rapid decrease in bit performance and advance.

Bit M-12 had an on-edge orientation, with the edge normal to the cutting direction. Contact was parallel to the hard direction of a dodecahedral face. The orientation should be structurally strong, except for a weakness along the dodecahedral cleavage. Indications of diamond breakage and erratic performance occurred early on, breakage becoming accentuated at about 11.5 ft. Abrasion and polishing of diafollowed. monds Overall performance was approximately the same as for bits M-11 and M-15.

Bit M-13 tested the on-edge orientation with the edge parallel to the direction of motion, comparable to drilling along the soft direction of a dodecahedral plane. Diamond chipping and breakage occurred early during the test, giving high rates of advance, possibly because an edge was sweeping around a circle of small radius, causing torsional forces to act along it. Flats were formed by chipping, followed by abrasion, polishing and a rapid decline in bit performance. Drilling characteristics and advance were very similar to bit M-15.

Bits M-16 and M-17 were set with the stones on edge, this being parallel to the radii drawn from the bit centre. The orientation is similar to M-12, but the diamond is at


22 deg. negative rake off the dodecahedral plane, giving a positive rake off the cube face. This results in a strongly backed orientation and fast drilling characteristics. A long cutting edge is combined with a structurally strong orientation, a gouging or planing action in drilling and diamond wear along the hard direction off the dodecahedral face. Over twice the advance rate of the other bits was obtained, i.e. 37.2 and 35.6 ft. respectively. Drilling performance was uniform, with slow, gradual abrasion or chipping of

the exposed edges and little fracturing or breakage of individual diamonds, in spite of fine hairlike cracks and other points of incipient weakness. Eventually the edges chipped or abraded to a degree at which increased surface contact would not permit sufficient penetration of individual diamonds to maintain the set minimum rate of .3 to .5 in./ min. at the maximum thrust of 1,595 lb.

Cube shaped diamonds do not require the compromise setting for increased bit life and drilling rate and decreased

diamond wear required for octahedral diamonds. Diamond loss after salvage was .0028 ct./ft. for bit M-17 and .0148 ct./ft. for M-16, as one diamond broke and fractured others just before the end of the run. All diamonds from these two bits could be re-used. The cube shape has the advantage of having eight similar edges for resetting.

The cube-shaped Congo industrial diamond appears superior to the Congo octahedron for drilling rate, footage and diamond loss, as it presents well supported cutting edges at 90 deg. angles. The octahedron has points with acute 70 deg. angles which are weak and break easily or edges with 110 deg. angles which are unsuitable for rock penetration.



Orientation of cube shaped diamonds

DIAMOND WEAR AND TEST RESULTS

EXT Bits	M-11	M-12	M-13	M-14	M-15	M-16	M-17*	Operations	Octahedron Bits M-1/M-9	Cube Bits M-11/M-17
Ft. drilled	18.68	16.96	14.93	13.72	15 · 27	37-20	35.62	Min. ft. drilled per bit	4.0	13.7
Diamond wt. in ct. Original Final	3·76 3·36	3·76 3·37	3·48 3·16	3·50 3·28	3·58 3·19	3-50 3-15	3·53 3·43	Max. ft. drilled per bit Average ft. drilled per bit Av. drill rate, all bits, in./min.	21·5 12·1 0·5	37·2 21·8 0·65
Salvage (re-usable) Diamond loss in ct. Net from wear Total after salvage	0·40 0·69	0·39 0·77	0·32 0·41	0·22 0·29	0·39 0·86	0-35 0-55	0·10 0·10	Av. drill rate, bits with pre- ferred orientation, in./ min. Max. diamond loss, ct./ft. Min. diamond loss, ct./ft.	0·9 0·086 0·012	1·2 0·056 0·003
Performance ct./ft. Net from wear Total after salvage		0·0230 0·0453				0.0028		Diamond loss, bits with preferred orientation, ct./ft.	0.030	0.009

[•] Same as M-16

MACHINERY AND EQUIPMENT

Locomotives for Spanish Mines

Six locomotives have been supplied by Robert Stephenson and Hawthorns, Ltd., to the Rio Tinto Company, Ltd., for service at the latter's mines in Spain. The locomotives are designed to draw loads of 295 tons at 10 m.p.h. and 350 tons at 5 m.p.h. on a 2 per cent grade.

The locomotives are of 3 ft. 6 in. gauge and are of type 2-6-0 superheated with tender. The two cylinders are of 17 in. diameter by 24 in. stroke and the wheels coupled have a diameter of 3 ft. 6 in. The total wheelbase is 17 ft. 9 in., and the weight of the locomotive in working order is 51.5 tons.



One of the six locomotives supplied to the Rio Tinto Company for its mines in Spain

The boilers are of the Belpaire type with welded inner firebox and steel tubes, fitted with superheater equipment. Boiler mountings include the Vacuum Brake Company's 19 m.m. S.J. (P) type combination ejector, Ross safety valves, Klinger KD water level gauges, "Everlasting" blow down cock and Gresham and Craner self-acting underfootplate ejector. Boiler pressure is 200 lb. p.s.i.

The locomotive frames are of steel plate and manganese liners are fitted to horn guides and axleboxes. The tractive efforts of each unit at 85 per cent WP is 28,074 lb. Tenders have wheels of 3 ft. diameter, with 3,100 gal. tank capacity and $5\frac{1}{2}$ tons coal capacity. They weigh $33\frac{1}{2}$ tons in working order. Thus the total weight of engine and tender in working order is 85 tons. The total length of the two units, over buffers, is 47 ft. $4\frac{1}{2}$ in.

Rubber and Plastic Conveyor Belting

Presented by the manufacturers, Barrow Hepburn and Gale, Ltd., as a cheap and effective type of conveyor belting for mine and quarry use, the Mitcham brand of rubber and canvas conveyor belting is claimed as swift and resistant to impact, as well as providing a minimum power consumption and the ability to deliver uniform amounts of material at controlled speeds.

Particular attention is paid during construction to the canvas body wherein lies the intrinsic strength of the belt, and belts produced by the manufacturers are normally made from 28, 32, 36 or 42 oz. duck. Stripped plybelts are also manufactured. Rubber covers are compounded according to the grade required. In the A grade belt the tensile figures are in the region of 3,700 lb. p.s.i. with an elongation of 550 per cent, and adhesion of rubber to plies is 24 to 26 lb. The B grade belt has a tensile strength of 3,000 lb., elongation of 450 per cent and ply adhesion of 20 to 22 lb.

Research into the damage caused to belts by sharp and abrasive materials has led to the development of the Mitcham Cushion Belt. The cushion surrounds the canvas body and is vulcanized to it, providing a resilient shock absorber between the carrying and pulley faces and the actual body. A particular cushion belt showed, under test, an average tensile strength of 4,000 lb. p.s.i., an average elongation of 695 per cent, a ply adhesion of 28 lb. per in. width, and an average adhesion of cushion to body of 26 lb. per in. width.

"Plyastic" fire-resisting belt is made from standard 32 oz. duck which, after being impregnated with a P.V.C. compound, is produced as a conveyor belt having .035 in. of plastic cover

on each side. These fire-resisting properties provide safe operation in mines and collieries where risk of fire exists, the plies, cover and edges being welded into one solid piece. Adhesion between plies is 28 lb.

Although the nature of the material transported and the tonnage carried has a marked effect on the maximum speed of a belt, a conservative estimate shows the recommended maximum speeds for Mitcham belting to be 300 f.p.m. at 12 in., 14 in. or 16 in. belt width, 350 f.p.m. at 18 in. or 20 in. belt width, 400 f.p.m. at 22 in. or 24 in. belt width, 450 f.p.m. at 26 in. or 30 in. belt width, 500 f.p.m. at 32 in. or 36 in. belt width, and 550 f.p.m. and 600 f.p.m. at 42 in. and 48 in. belt width respectively. Mitcham conveyor covers are made in grades A, B and C and heat resisting.

Vehicles for Oilfield Use

The latest type of vehicle to be ordered by the Shell Petroleum Company, Ltd., for operational use in the oilfields in Venezuela, Colombia, Seria (British Borneo), and Indonesia, is the 6-wheeled 6-wheel drive Constructor, supplied by Messrs. Scammel Lorries, Ltd. The Constructor chassis will operate in these oilfields with different wheelbases to suit several types of body work and equipment. All have been adapted to the special requirements and the total order covers 38 vehicles and the first of 14 for Venezuela left the U.K. on March 10.

The Constructor now being supplied has many features, including a wheelbase of 15 ft. 9 in. for operation in conjunction with heavy duty semi-trailers. This unit has a Darlington model 80 winch and special reversing drive utilizing the six speeds of the gear box, which enables the winch to be operated in a forward or rearward rotation whilst the vehicle is moving in either direction. The tyre equipment is 13.00 x 24 in. all round with twins on the rear axle.



The Scammel 6 x 6 Constructor chassis

These vehicles are powered with the Rolls Royce C6.NFL 6-cylinder diesel engine or, for less arduous conditions, the Meadows 6DC-630 6-cylinder diesel engine. The 6-speed main gear box and the transposing box affords 12 forward speeds and two reverse speeds. Each axle is of the double reduction spiral bevel epicyclic type and each is driven by an independent propellor shaft. The rear bogie and the suspension is located by torque arms and radius links, affording full articulation whilst relieving the springs of all driving and brake reactions or twisting effects. The manufacturers claim that the units give an effective performance under cross-country conditions.

A Tong Loader for Longwall Faces

A device, developed at Middleton Broom Colliery, near Leeds, for gathering cut and blown coal on longwall faces, consists of two side plates, 5 ft. long by 1 ft. high, hinged at one end to a wedge-shaped head, and connected by toggle bars to a central traction bar which runs freely through the wedge head. To the ends of this traction bar are connected

the main and tail ropes of a double drum haulage unit, the tail rope passing from the head end of the bar, round a return wheel at the end of the face, and back to the haulage.

When the tail rope is pulled the arms close and the tongs are pulled into the loose coal. Upon reversal, and pulling with the main rope, the arms are forced open by the toggle bars, collect all loose coal in their path, and carry it to the delivery point. As at present designed, the loader gathers about 8 cwt. of coal on each run, but the size can be adjusted to suit local conditions.

A Fabricated Pipework Skip Hoist


Tubular constructions have gained an increasing use in modern engineering application, and The Tubewright, a new film published by Stewarts and Lloyds, Ltd., now outlines the progress in both manufacturing techniques and the uses of tubular steel. The high strength to weight ratio of hollow structural members is demonstrated with marked success in this instructive and enjoyable film, and despite the fact that steel tubes as structural members have been used in heavy industry in many applications, a most interesting use from the point of view of the mining engineer is in the construction of a skip bridge at Bilston Iron and Steel Works.

In this example of fabricated pipework construction, a new blast furnace was needed at a spot where an existing skip bridge was footed. A considerable engineering problem arose owing to the fact that two blast furnaces were to be maintained in operation while the existing skip bridge was demolished, the work involving the erection of a new skip bridge by a method which would allow this principle to be followed.


The answer was found to lie in the vertical fabrication of the tubular framework, which allowed for speedy construction. This in turn presented as few limitations to output as was possible under the circumstances. This entire structure was welded with the exception of top and bottom pins, and some of the welds had to be run 80 ft. above ground level.

It took only a few months for the new skip bridge to be in operation for blast furnace charging.

It may be recalled that the jib of the Ransome and Rapier



The skip bridge being threaded between stoves and furnace



A view of the skip hoist platform from the wheeling platform

W1400 walking dragline, described in *The Mining Journal* of November 9, 1951, was constructed of steel tube in order to emphasize the weight requirements of the bucket.

Tubular steel thus provides many applications, from the lighter structures (such as racks and frames of all types manufactured by Tubewrights, Ltd., a subsidiary company, and which may be visualized as fulfilling a need in the larger mine storeroom) to the impressive bridges already constructed in various places in the United Kingdom and the cranes and other equipments used in heavy industry.

A Versatile Industrial Compressor Unit

A pedestal-mounted compressor unit, the 200 SAS, is now in quantity production by The Hymatic Engineering Company Ltd. With a displacement of 5.25 c.f.m. at 750 r.p.m. and a working pressure of 100-150 p.s.i., the 200 SAS may be incorporated as initial equipment or as an optional extra on tractors, special vehicles, machine tools and powered plants of all kinds for suen duties as pneumatic greasing, the operation of pneumatic tools, braking systems, jigs and fixtures and other compressed air applications. When necessary the unit may also be operated at 1,000 r.p.m. to give a displacement of 7 c.f.m. against a working pressure of 100 p.s.i.

The single 200 c.c. capacity, high-duty cast iron cylinder, bore 2.67 in. and stroke 2.16 in., is of the single-stage type heavily finned so that in conjunction with the finned cast aluminium cylinder head and the generous inlet and outlet ports, a consistently low delivery temperature is maintained. Weighing 38 lb. complete, the unit absorbs about 1 h.p. at 750 r.p.m.

Summer School in Mineral Dressing

A Summer School in Mineral Dressing will be held in the Bessemer Laboratory, Royal School of Mines, Prince Consort Road, London, S.W.7, from Tuesday, September 14 to Friday, September 17, 1954. The course includes lectures covering comminution, classification, grinding control, gravity separation, flotation and ancillary processes and is illustrated by films, demonstrations and class work.

METALS, MINERALS AND ALLOYS

COPPER.—American producers are reported to be concerting a big reduction in the output of the metal in view not only of the apparent industrial recession, but in preparation for the important additions to be expected during the current year from new mines opened with government price support. It is estimated that the Anaconda and Kennecott subsidiaries in Chile have reduced current monthly output from the 29,500 s.tons obtaining in the latter part of last year to about 20,700 s.tons. At the same time U.S. domestic production is computed to have been reduced to some 14,500 s.tons a month, and the world output to have been cut from 206,000 to 182,500 s.tons monthly—with consumption estimated at 175,000-185,000 s.tons monthly.

What the attitude of the Chilean authorities will eventually be to these cuts is yet to be learned, although formal applications for curtailment have so far been rejected. However, as there is a large surplus of Chilean copper still unsold, possibly of the order of 80,000-100,000 tons, as well as the current monthly production, they will probably not have much option but to agree to them. It is not so very long ago that concerted action by U.S. producers to cut production in order to maintain prices would have invited the attention of the Department of Justice under the anti-trust Acts, but we cannot see the U.S. Administration moving in this direction to-day.

As regards new mines coming into production during the current year, Anaconda's Yerington property is said to be already producing at the rate of 33,000 s.tons yearly, while the A.S. and R.'s Silver Bell is expected to follow before the end of June with an annual rate of 18,000 tons. Soon after that, the Phelps Dodge Lavender Pit is due to commence production at the annual rate of 38,000 tons, to be followed by the White Pine property with 35,000 tons annually in October and Miami's Copper Cities property ready to produce at the rate of 32,500 tons by the end of the year. These additions will, it is estimated, contribute some 12,000 s.tons a month to the U.S. domestic supply, unless prices should fall to a figure below the government's guaranteed floor price of from 22 c. to 25½ c. per lb.

The Chilean Government has announced that 10,000 tons of its copper stocks have been sold in Great Britain at the world market prices with payment to be made in sterling. Other countries, like Germany, are also reported to be in the market but on a barter basis.

It is understood that an agreement has been reached for increasing the railway freight for the transport of copper from the Copperbelt to the port of Beira by 30 per cent. Decline in railway revenues is said to have led to a widespread demand for a general increase in rail charges.

LEAD.—On Thursday of last week the St. Joseph Lead Co. raised their price to 13½ c. N.Y., at which price a good consumer demand resulted. The rise was largely inspired by the expected stockpiling purchases in America.

U.S. consumption in January was 88,700 s.tons against 83,708 s.tons in December. Shipments of automotive replacement batteries for the first two months of the year are well above the figures for the corresponding period of 1953 and 1952. The future of the automobile trade in the States, however, is still considered uncertain.

ZINC.—The advance in the U.S. lead prices is said to have given the market a somewhat firmer tone, but the quotation is again unchanged at 10.25 c. E. St. Louis. A fairish demand from consumers continues, but there was no major feature.

It is reported from Japan that price reductions are under consideration, due to expanding output and the tight money situation.

TIN.—The tin market maintains its volatile character and at the beginning of the week the price of cash rose £18 5s. per ton to £754-£755 and three months gained £9 £719-£720, increasing the premium in cash to £35. Subsequently prices went higher (see Metal Exchange report).

In the U.S. the advance was not followed, partly on account of the end of the N.Y. dock strike and partly because the London advance seemed overdone. The price on Wednesday was 95 c. per lb.

The following are the Tin Study Group's production figures for the first two months of the year:

Country	February 1954	JanFeb. 1954	JanFeb 1953		
Belgian Congo	404	696	2,174		
Bolivia*	2,268*	2,268*	1,470*		
Indonesia	2.247	4,792	4,712		
Malaya	4,277	9,385	9,305		
Nigeria	635	1,354	1,591		

[·] Figures relate to January only.

The most notable feature is the Congo output which at 696 tons compares with 2,174 in the corresponding period a year ago.

Bolivian exports in January are given as 2,268 tons as compared with 1,470 tons in the first two months of last year. The Bolivian Government was said to have authorized the Banco Minero to pay "remunerative prices" and to encourage the production of tin, wolfram, antimony, copper, gold, asbestos and sulphur to maintain production in private mines and to avoid unemployment.

ALUMINIUM.—According to Alcoa's development division, the automobile industry is expected to play an important part in the expansion of aluminium consumption to the U.S. Present consumption per car is estimated at about 20 lb. but already an average of 125 lb. is forecast for the not too distant future. On an output of 6,000,000 automobiles a year consumption might expand to some 300,000 s.tons. Increased use is expected not only in engines, but in transmission, radiators, electrical equipment, brakes, and general trim.

Secondary aluminium smelters in the U.S. are much exercised by the heavy exports of scrap, especially to Japan and West Germany and this has caused an advance in price of secondary alloys. In consequence secondary smelters are requesting remedial action.

U.S. production of primary aluminium in February is reported by the Aluminium Association at 110,483 s.tons, an increase of 20 per cent over February a year ago.

The new Norwegian aluminium plant at Sunndalsora is expected to begin operations this month although full production may not be achieved until next year owing to delays with the hydro-electric plant. The capacity is rated at around 40,000 tonnes a year, which will be additional to the current output of some 52,000 tonnes. Most of the cost has ben supplied by a loan from the American E.C.A. to be repaid in aluminium deliveries.

According to a report by the President of Pechiney, French exports were trebled last year by sales to Britain and the U.S. Domestic demands had been slow up to the fourth quarter, but then revived, and orders have been booked for the whole output for the first half of the current year and over a portion of the second.

The Australian Commonwealth Minister of Supply stated earlier in the week that the Tasmanian aluminium plant would be put into commission next January. Projected output is 13,000 tons of ingots annually, sufficient for Australia's present needs.

MAGNESIUM.—The Dow Chemical Company have made cuts in their price of magnesium sheet and plate, ranging between 5 per cent and 28 per cent. The demand for magnesium is said to have increased sharply and with these lower prices it is hoped the metal will be more competitive with aluminium.

QUICKSILVER.—The U.S. price of quicksilver was further advanced at the beginning of the week to \$212 to \$215 per flask. The London price has also advanced and yesterday stood at £77½.

TUNGSTEN.—The Korean Tungsten Company has ordered all mines in Korea to shut down, with the expiration of the Korean-U.S. Tungsten Agreement on March 31. World prices recently were only a third of what the U.S. was paying under the Agreement. Over 4,000 miners are said to have been laid off. Partly no doubt as the result of this shut-down and partly as a result of consumer restocking as the price bottomed last

month, the Ministry of Materials again advanced its selling price from Tuesday last to 165s. per l.ton unit and of scheeling to 160s. In the U.S. the price was advanced at the beginning of the week to \$18-20 per s.ton unit.

GOLD.—A Senate banking sub-committee had under review last week several Bills relating to gold. These variously proposed a restoration of the pre-1933 gold standard; convertibility of paper dollars and gold coins; the establishment of a free domestic market; and an increase in the official gold price of \$35 per oz. The Deputy Treasury Secretary, Mr. Burgess, and the chairman of the Federal Reserve Board both spoke against the proposals, which they regarded as a desirable achievement one day, but they saw no advantage to be gained by their adoption at the present time, and thought that the U.S. should defer consideration until other major countries were ready to do so also. Mr. Burgess believed that gold released in the U.S. might simply be hoarded and become a tool for international speculators.

The speakers have since been reminded by the Press that they accepted the appointment from an Administration which promised in its platform a return to a redeemable currency. At present however, gold, as the policeman of the politician, can hardly expect a welcome from the same Administration.

Iron and Steel

Still enjoying almost complete immunity from the causes which have set back the rate of production in Western Europe and precipitated a pronounced recession in the U.S.A., the iron and steel industry of Great Britain is in a flourishing condition. On this occasion the hesitations which usually develop in the pre-Budget period has been so slight as to be almost imperceptible. A key note of confidence was sounded in the Government's Economic Survey for 1954, and the twin targets of the steel industry are the further development of productive capacity and the expansion of exports.

To that end export premiums have been severely pressed and in the case of merchant bars have been abolished altogether, whilst home prices have been kept unchanged although under inflationary pressure. Of the export trade the best that can be said is that it has not declined, but the home market is brisk and buoyant. Blast furnace capacity is fully extended to keep pace with the swollen demand for pig iron. About 70 per cent of the total output comprises basic iron for the steel plants yet still more is wanted and completion of new blast furnaces is being pressed forward with all possible speed. Haematite production is fully absorbed and only foundry iron is still freely obtainable. (Merchants claim to be delivering bigger turnovers of ferrous scrap, but it is noticeable that since November last reserve stocks have been reduced by over 50,000 tons and are still falling.) Ample tonnages of British steel series are now available and this has led to a very severe curtailment of imports. The almost total loss of the British market for billets, sheet bars and slabs is viewed with all the greater concern by Continental producers since there is every indication that this is a permanent change and not merely a temporary phase.

The London Metal Market

(From Our Metal Exchange Correspondent)

The outstanding feature of the week has been the sharp rise in the price of tin which has been accompanied by very good turnovers. The rise has been brought about by increased consumer interest on both sides of the Atlantic, which has been accompanied by the realization that the conclusion of the Agreement in respect of the third year of the Indonesian/American contract will retard the surplus production having an effect on world prices. There have also been rather more optimistic rumours about the possibilities of consumer countries signing the Tin Agreement. On Thursday morning the Eastern price was equivalent to £738½ per ton c.i.f. Europe.

Interest in lead and zinc has been almost non-existent, and, as can be expected under such circumstances, prices have tended to drift downwards. The technical position of lead, however,

is such that the backwardation is likely to remain at, or above, its present level throughout the month.

The copper market has been filled with rumours about sales of Chilean copper, but in spite of this prices have been maintained owing to good demand on the Continent and the reluctance of producers to sell forward metal at any reasonable discount from the quotation for spot material. For instance, most producers are still asking the equivalent of 29½ c. per lb. f.a.s. for May shipment. There is no doubt that the sales which the Chileans have made in recent weeks to the U.S., the U.K., and some other European countries have gone a long way towards easing their foreign exchange position, and, therefore, they are no longer so interested in disposing of metal at a price below to-day's level. In fact, it can be said that the future of the copper price is more bound up with the overall financial position of Chile than with any statistics dealing with the metal itself

Closing prices and turnovers are given in the following table:--

	Apri	1 2	Apr	il 9
	Buyers	Sellers	Buyers	Sellers
Tin				
Cash	£732}	£7371	£7621	£765
Three months	£705	£706	€727}	£728}
Settlement		371	£7	
Week's turnover	280	tons	630	tons
Lead				
Current month	£934	£94	£921	£921
Three months	£914	£913	£901	163
Week's turnover	6.000	tons	3,825	tons
Zinc	.,			
Current month	£794	£801	£79	£791
Three months	£784	£784	£774	£78
Week's turnover		0 tons	4,975	tons
Copper	4			
Cash	£233	£234	£2364	£2374
Three months	£227	£227‡	£228}	£229
Settlement	£2	34	£23	374
Week's turnover	5,80	0 tons	5,950	

OTHER LONDON PRICES - APRIL 8

ANTIMONY

English (99%) delivered 10 cwt. and over	ea,		£210 per ton
Crude (70%)			£200 per ton
Ore (60% basis)			22s./24s. nom. per unit, c.i.f.
	N	IICKI	EL

99.5% (home trade) £483 per ton

OTHER METALS

Aluminium, 99.5%, £156 per ton Bismuth	Osmium, £50 oz. nom. Palladium, £7 10s. oz.
(min. 4 cwt. lots) 16s. lb.	Platinum, £30/£31
Cadmium (Empire), 13s. lb.	Rhodium, £43 10s. oz.
Chromium, 6s. 5d./7s. 6d. lb.	Ruthenium, £23 oz.
Cobalt, 20s. lb.	Quicksilver, £77.10s.
Gold, 248s. 10½d. f.oz. 1	ex-warehouse
Iridium, £55 oz. nom.	Selenium, 35s. 9d. nom.
Magnesium, 2s. 10½d. lb.	per lb.
Manganese Metal (96%-98%) £225/£262	Silver 73\{\frac{1}{2}d\}, f.oz. spot and 73\{\frac{1}{2}d\}. f'd.
Osmiridium, £40 oz. nom.	Tellurium, 15s./16s. lb.

ORES, ALLOYS, ETC.

UKLS, A	LLUI	is, Eic.
Bismuth		60% 8s. 3d. lb. c.i.f. 50% 7s. 3d. lb. c.i.f.
Chrome Ore—		
Rhodesian Metallurgical (lun	npy)	£14 5s. 6d. per ton c.i.f.
" " (concentra		£14 5s. 6d. per ton c.i.f.
Baluchistan Metallurgical		£15 19s. 6d. per ton c.i.f.
Magnesite, ground calcined		£26-£27 d/d
Magnesite, Raw		£10 - £11 d/d
Molybdenite (85% basis)		102s. 4d103s. per unit c.i.f.
Wolfram (65%)		World buying 160s. nom.
3		165s. U.K. Selling
Scheelite (65%)		World buying price nom.
_ ** ** **		160s. U.K. Selling
Tungsten Metal Powder (98% Min. W.)		14s. 3d. nom. per lb. (home)
Ferro-tungsten		11s. 3d. nom. per lb. (home)
Carbide, 4-cwt. lots		£35 13s. 9d. d/d per ton
Ferro-manganese, home		£53 10s. 0d. per ton
Manganese Ore Indian c.i.f. Eur	rope	
(46%-48%)		7s. 4d 7s. 9d. per unit
Brass Wire		2s. 4 d. per lb. basis
Brass Tubes, solid drawn		1s. 8 ³ d. per lb. basis

THE MINING MARKETS

(By Our Stock Exchange Correspondent)

Contrary to usual form, stock markets proved buoyant prior to the budget. The rise of \$102,000,000 in the gold reserves of the sterling area during March and the strength of sterling abroad helped this trend. After the budget, prices were marked down as a precautionary measure, but rapidly recovered on the appearance of buyers. While there must naturally be some individual disappointment with the Chancellor's proposals, the budget is obviously financially sound and healthy for the country's economy. Clearly, no risks have been taken for the sake of political popularity.

Kaffirs spent the week digesting the March returns and this led to rises in Consolidated Goldfields, West Rand Investment Trust and Johnnies. A much healthier atmosphere was reported on the Johannesburg Stock Exchange. There was more confidence in the future and locally it was hoped that reductions in taxation will lead to prosperity and a higher level of invest-

ment.

Individual mines were influenced by the returns, but in some cases much less than expected. Randfontein rose despite the loss on gold production. Hopes of excellent uranium figures ran high. Western Reefs hardened following the report, but many of the older mines lost ground. The promising results from Doornfontein and Blyvooruitzicht Gold Mining had little influence on share prices.

The Orange Free State section was again the main centre of interest although there was a tendency to tail off towards the end of the period. There was some speculation in the Freddies Group at their lower price level. The steady progress of St. Helena and its continually increasing profits contrasted favourably with results from the above mines and Welkom. This was reflected in the share price. Geoffries, Ofsits and President Brand also returned to favour. News concerning Virginia and Merriespruit was received from the Kennecott report. This American company has considerable interest in both mines. It is anticipated that production on an initial scale of 50,000 tons

a month will begin at Virginia in the first half of 1954. Work has also started on the uranium plant. The No. 1 shaft on Merriespruit was equipped last year and the sinking of No. 2 shaft, temporarily postponed, will be resumed during 1954. The shares of both companies advanced on the news.

Business in the West African market was quiet but there was a firmer undertone. Leaders hardened where changed. Ashanti recorded a sharp gain following the excellent development result on the 35th level. In one cross-cut, values of 151 dwts. over 15.5 ft. were obtained. It is a curious fact that results such as this in the O.F.S. market would probably send the share concerned "through the roof." Konongo rose due to favourable press mention.

Diamond shares improved sharply. So far the American recession appears to have had little effect upon sales.

Coppers were better, taking in their stride higher local rail charges in Rhodesia and the sale of 10,000 tons of Chilean copper in the United Kingdom. Helping factors here were the improvement in the commodity price and the lower Chilean output. Roans responded to the ending of the strike on the property. Tanks were again a good market on continental buying.

Eastern tin shares were quiet despite the better cash price for the metal. Pengkalen, however, achieved an outstanding jump due to a Press tip, and buying on a narrow market. In the Nigerian section, changes were unremarkable, although most columbite producers were slightly harder. Beralts improved on the better tungsten price.

Lead/zinc shares altered little. Rhodesia Broken Hill, however, rose, on the announcement of plans to overcome the lower commodity prices by higher production. Another good feature in this section was San Francisco Mines. Asbestos shares and Consolidated Murchison attracted buyers and Canadian shares were better, especially for base metals. The poor Hollinger figures depressed the share price.

		1+ or -		Price	+ or -			+ or -		Price	1+ or -
INANCE		on week		April 7	on week	MISCELLANEOUS GOLD	April 7	on week	TIN (Nigerian and	April 7	
frican & European	276	-16	Freddies	7/3	+6d	(contd.)			Miscellaneous) contd.	repres .	011
nglo American Corpn.	61		Freddies N	7/74		St. John d'El Rev	20/9	3.4	Geevor Tin	11/-	-
nglo-French	18/9	+60	Freddies S	7/74		Zams	34/3	1 24	Cald & Day Mark		-
nglo Transvaal Consol.	21/3	-3/9	F. S. Geduld	44	7.724	Zains	34/3	+30	Gold & Base Metal	3/6	****
Central Mining (£1 shrs.)	29/6		Geoffries	15/-	1 1/2	DIAMONDS & PLATINUM		1	Jantar Nigeria	9/11	+1
	50/-						51	1	Jos Tin Area	13/3	
onsolidated Goldfields			Harmony	31/6	6d	Anglo American Inv		+ 16	Kaduna Prospectors	2/44	
Consol. Mines Selection	29/41		Loraine	11/3	*****	Casts	25/-	+1/6	Kaduna Syndicate	2/41	
ast Rand Consols	3/-	-1½d	Lydenburg Estates	16/3	-3d	Cons. Diam. of S.W.A.	5		London Tin	6/-	-1
General Mining	313		Merriespruit	12/74	+104d	De Beers Defd. Bearer	81/3xD	+2/6	United Tin	3/3xD	i
I.E. Prop	38/9	1	Middle Wits	14/14	1 410	De Beers Pfd. Bearer	163		Cinted Int	3/340	
enderson's Transvaal.	7/9	+3d	Ofsits	51/3	11/2	Pots Platinum	8/9		SILVER, LEAD, ZINC		
ohnnies	45/9	12/0	President Brand	51/3	11/3	Watervaal	13/6		Broken Hill South	2.11	
	31	12/2	President Brand		+1/9	waterwaar	13/0	730		2弘	+
land Mines			President Steyn	33/6		CARRER			Burma Mines	2/6	
and Selection	34/41	/ 10	St. Helena	24/9	+3d	COPPER	69/9	+1/104	Consol. Zinc	30/71	1 +7
trathmore Consol	31/3	-1/3	Virginia Ord	13/44	+44d	Chartered			Lake George	7/6	-
nion Corp. (2/6 units)	30/-	+6d	Welkom	19/9	+6d	Esperanza	7/41	1 ± d	Mount Isa	37/6	
ereeniging Estates	447		Western Holdings	44		Indian Copper	4/6	*****	New Broken Hill	24/3	-
rits	36/3	+9d		. 8	32	Messina	37	-16	North Broken Hill	27	
Vest Wits	43/14	+71d				Nchanga	7-4	+ 32	Rhodesian Broken Hill	1016	11
Vest Wits	49115	7 /24	WEST AFRICAN GOLD			Rhod. Anglo-American		+11d	Knodesian Broken Hill		
			Amalgamated Banket.	1/74	+148		13/3			23/11	+2
AND GOLD		12		5/9				1	Uruwira	3/101	+
lyvoors	36/9		Ariston			Rhodesian Selection	16/9	+9d	*********		
rakpan	10/3	-3d	Ashanti	21/11		Rhokana	204 XD	-8	MISCELLANEOUS	1	
ity Deep	17/6	74d	Bibiani	4/71	+6d	Rio Tinto	23 3	32	BASE METALS & COAL		
onsol. Main Reef	18/9		Bremang	2/-		Roan Antelope	17/-	+74d	Amal. Collieries of S.A.	42/3	
Olisoi. Main Reci			G.C. Main Reef	3/6	+114	Selection Trust	37/3		Associated Manganese .	46/-	1
rown		*****	G.C. Selection Trust	6/3		Tanks	72/3	1.1/0	Cape Asbestos	26/3	+1
Daggas		+ 12	Konongo	2/74	2 4 4 4 2 4		57/6	1 2/0	C.P. Manganese		
Doornfontein	26/6	+60	Konongo		+30	Tharsis Sulphur Br	3//0	+3/9	C.F. Manganese	58/9	
Durban Deep	37/6		Lyndhurst Deep	1/-	*****	TIM (F4)			Consol. Murchison	42/6	+
B. Daggas	13/3	3d	Marlu	1/6	*****	TIN (Eastern)	2016	2.4	Mashaba	44	
E. Geduld (4/- units)	30/-	+6d	Taquah & Abosso	2/74	+140	Ayer Hitam	25/6	-3d		213	
E. Rand Props	23			-1-6	1 . 24	Gopeng	8/1½XD		Rhod Monteleo	1/0	1
	2 h					Hongkong	7/9	3d	Turner & Newall	16/-	+
Geduld		-3d	AUSTRALIAN GOLD			Ipoh	16/3		Wankie	13/3	
Govt. Areas				2/9		Kamunting	8/3		Witbank Colliery		
Grootvlei		+4½d	Cald Miner of Valer Il-			Kepong Dredging	4/9		Witoank Comery	318	
ibanon	12/6	3d	Caset Davidsa Dass	8/3xD			10/6		CAMADIAN A		1
uipaards Vlei	23/9	+3d	Great Boulder Frop					*****	CANADIAN MINES		1
Marievale			Lake View and Star	13/3	-36	Malayan Dredging	26/-	-3d	Dome	\$29\xE	
Modderfontein East	15/-		Mount Morgan	17/-		Pahang	13/71	1½d	Hollinger	\$24	1
		71.4	North Kalgurli	7/-		Pengkalen	8/9	+1/3	Hudson Bay Mining	\$79	
New Kleinfontein		-/40	Sons of Gwalia	6/14		Petaling	8/14	+ 3d	International Nickel	\$683	1
New Pioneer		30	South Kalgurli	- 7/-		Rambutan	15/-		Mining Corpn. of Canada		
tandfontein		+4/6	Western Mining	11/3	2.3.5.5		8/3	*****			-
Robinson Deep	17/-	+60	western winning	11/3	+30	Siamese Tin		*****	Noranda		
tose Deep		-30				Southern Kinta	16/6		Quemont		
immer & Jack			MISCELLANEOUS GOLD			S. Malayan	24/41	+41d	Yukon	3/9	
		71.4	HISCELLANEOUS GOLD			S. Tronoh	8/9			1	1
.A. Lands		-/20	Cam and Motor	9/3	-110	Sungei Kinta	11/-		OIL		
prings		-110	Champion Reef	4/41		Tekka Taiping	6/-	1.34	Anglo-Iranian	113	1
tilfontein		+110	Falcon Mines	7/74	141	Tekka Taiping			Apex		1
ub Nigel		-740	Globe & Phoenix	22/6	1 424	Tronoh	22/3	+30	Attock	44/41	
an Dyk		-60	G.F. Rhodesian	5/3					Daniel	44/41	
enterspost			London & Dhodoin	3/3		TIN (Nigerian and	-		Burmah	80/-	1
		******			+150	Miscellaneous)			Canadian Eagle	31/3	
lakfontein		-30	Motapa		*****	Amalgamated Tin	14/-	+140	Mexican Eagle	20/14	-
Vogelstruisbult		+60	Mysore	4/6				+1/9	Shell (bearer)	54	1
West Driefontein		+4	Nundvdroog	5/41	*****			1 111	Trinidad Leasehold	20/2	
W. Rand Consolidated		+ 1	Ooregum	3/6				T120	T P D	20/3	-
Western Reefs		± 1/0	Oroville		*****			30	T.P.D	24/9	
TY USECALI PLOUIS	2013	1 71/2	CIOTHE	16/4	-14	Ex-Lands Nigeria	3/3	+140	Ultramar	29/6	1

COMPANY NEWS AND VIEWS

Rand and O.F.S. Returns for March

Higher tonnages sent to the mill by Rand and O.F.S. pro over the short month of February. This has enabled costs to be decreased and in many cases higher working profits are reported. But these factors do not reflect the whole picture and it is particularly noteworthy to record that better results have been obtained despite a lower gold price which was 247s. 9d. per f.oz. against 248s. in February and 248s. 2d. in January.

	M	arch, 19	54	ends	Cur	rent Fina Year	Year			
					T	otal to D	ate	T	otal to D	ate
Company	Tons	Yield	Profit	7	Tons	Yield	Profit	Tons	Yield	Profi
Gold Fields	(000)	(02.)	(2000)		(000)		(£000)	(000)	(oz.)	(£000
Doornfontein	50	14,998 19,915	66.0	3	229	66,929 161,891 177,782 18,285	224-5	770	147 004	200
Libanon	97	19,913	53·2 43·9	3	792 956	101,891	416-9		147,604 171,701 17,409 53,566 58,906 203,590 212,917 39,244 69,993 176,121	373
uipaards Vlei	110	20,934	24.4		81	19 305	368·4 71·0		17,701	438
Rietfontein		6,311 20,425	24.5	D	281	78 601	63.8		53 566	27
Robinson Deep . Simmer & Jack .		20,423	24.5	n	379	78,691 60,717 197,530 223,693	39.4		58 906	41
ub Nigel		21 945	97.6	1	596	197 530	901-2		203 590	1030
enterspost		25 984	59.6		955	223,693	516-3		212,917	548
lakfontein		20,642 21,945 25,984 13,706	72.7	D	113	40,424	214-8		39,244	210
ogels	103	25,651	107 - 2	D	304	76,455	320-2		69,993	277
West Drie	47	35,322	284 - 2	3	405	296,612	2393-1	265	176,121	1348
anglo American*										
Irakpan		19,672	21.5	D	329	57,493	55-8		60,058	57
Daggas	219	31,040	314.9	D	636	148,595 47,279	909-1		155,252	1018
ast Daggas	93	19,808	63.4	D	278	53 973	139-5		45,656	144
.A. Lands		51,040 15,808 18,333 18,269	7.1	D	387	53,873	24-1		54,329 61,268	158
prings	68	13 420	2.0	D	186	37 452	L 6-3		32,832	40
Velkom Vestern Hldgs	42	14.734	40.0	D	137	54,413 37,452 44,103	130-1	10/	34,034	40
West Reef Ex	115	13,420 14,734 22,796	66.5	D	332	66,077	194-7		65,689	246
Central Mining	100	60 400	400 4		000	****	4400			
Blyvoor City Deep Cons. M.R	102	31,498	470 - 1	1	880	518,487 92,702 210,400 128,237 85,109 128,126 17,436 116,581 30,976 36,999	4190-8	924	557,611	4739
ity Deep	175	31,800	18-0	D	483	210,400	193.4	472 1598	91,610	76
Cons. M.R.	284	25,820 45,165	48-1	1	1486 793	129 227	141-6		91,610 223,503 125,240 92,303 119,354 17,510	218
D. Roodepoort	100	30,193	52.1			95 100	141.7	537	02 202	245
East Rand Prop	196	44 501	115.3	D	560	128 126	337-9		110 254	295
Modder R	58	44,592 6,104	2.4			17 436	8-1		17 510	29
Modder B	117	13 446	13-6		1017	116.581	121-6	1037	119.813	188
Rose Deep	72	11,127	12.5	D	200	30,976	35.5		31.757	13
Rose Deep Welgedacht	34	11,127	2.1	3	302	36,999	23-1		119,813 31,757 37,483	40
J.C.I.*	1 20	2 240	× 22.0	-	70		T 400		12.124	١
Freddies N.†	33	6 264	L22-9	D	70 87	6,909	L 43.8	76	12,436	
Freddies S.†	40	6 151	L15-	P	109	16 369	L 48-3 L 47-4			-
Govt. G.M.A.	275	34,624	30	D	765	98,045	90-	726	08 151	180
Randfontein	318	41,182	L20	D	835	119,411			98,151 119,395	90
Union										
East Geduld		43,010	316-0			119,583	870-6		119,996	88
Geduld Prop	185	15,212	26-4	P		45,551	73-1	293	45,440	9
Grootvlei Marievale	66	16,681	220 - 5			47.654	618-0		116,889	698
St. Helena		17,658				50 832	148-9		44,088 36,063	
an Dyk		14,176		D	234	119,583 43,331 111,329 47,654 50,832 40,724	7-8	274	44,125	
General Mining					1					
N. Rand Cons.:	28 230	6,141	185					243	55,461 94,995	
Anglo		1 -		1					1,70	1
Transvaal					-					
N. Klerksdorp	172	20 211	L 0 · 9			247 660	L 3-	31 31 31 31	4,126	42
Village M.R.§	33	29,21	9.			247,660		7 304		12
Others										1
Illaton Gold N. Kleinfontein	109	7,586	34 -	D	315	17,471	49:	318	41,158	8
Nigel Gold	26		L 2.			39,682 12,996 7,813 71,354 34,978	L 54	5 95		
Spaarwater	10	2.67	0.	F	31	7.813	0.6		7,064	L
Stilfontein	78	2,671	136) [226	71.354	378-		46,207	
W. Nigel	17	3,832	8.	1 10	155	1	75-			6

Notes.—Profit figures are in all cases figures of working profit excluding profit from sale of gold at premium prices. In cases of groups marked with an asterisk(*) profit includes sundry revenue. Profit figures preceded by L indicates a loss. † Excluding development expenditure ‡ Including £165,000 from sales of uranium § Underground fire March 3 and 4 resulting in a loss of £2,371

Freddies Consolidated Mines

Further details have now been announced of the proposed merger of Freddies North Lease Area and Freddies South Lease Area.

A new company is to be formed and will be known as Freddies Consolidated Mines, having an authorized capital of £17,500,000 in £1 shares. The proposal is that the new £17,500,000 in £1 shares. The proposal is that the new company, Freddies Consolidated Mines, will take over the assets of Freddies North and Freddies South and will assume all the liabilities of both companies, which amount to approximately

£4,500,000 in each case—apart from the 5 per cent loan stock.

At the same time, Freddies Consolidated will issue 4,060,784 shares of £1 each to Freddies North, and 4,142,354 £1 shares to Freddies South at 25s. per share. Freddies North and Freddies South will be placed in liquidation and the above share distribution by Freddies Consolidated will be made to share-holders in the ratio of one new Freddies Consolidated for every three Freddies North or Freddies South held.

As previously announced, the outstanding loan of £3,500,000 made to each company jointly by Johnnies, Anglo American Corporation and De Beers Investment Trust, are to be be funded into shares and from the details now available it is revealed that this operation is to be carried out on the basis of 25s, per £1 Freddies Consolidated share. Thus, the £7,000,000 loan involved will be met by the issue of 5,600,000 £1 shares in Freddies Consolidated.

With regard to the position of the loan stock holders, they will be offered the right either to take payment for their stock in cash at £102½ per cent, or they can convert into Freddies Consolidated shares on the basis of 41 shares for every £50 of loan stock held. This conversion offer would, therefore, be on the same basis as the funding of the short term debt. If the amalgamation scheme is approved at the extraordinary general meetings of Freddies North and Freddies South to be held early in June, it is proposed that Freddies Consolidated will make a new issue of shares to holders pro rata to their existing holdings, which will provide a net amount of about £2,100,000.

Vaal Reefs Offer 4-for-3 at 16s. 8d.

Vaal Reefs Exploration and Mining has announced that its new issue of 5s. shares will take the form of a 4 for 3 offer at 16s. 8d. per share.

In accordance with the company's flotation agreement, West-ern Reefs and the Anglo American Corporation of South Africa will be offered the right to subscribe for a total of 300,000 new shares of 5s. each, at the same price as the shares are being offered to shareholders, namely 16s. 8d. per share.

The issue, which will involve 4,000,000 shares, has been underwritten by the Anglo American Corporation for a cash commission of 2½ per cent on the issue price. The offer is being made to shareholders registered at the close of business on

According to a circular to shareholders issued with the annual report covering the year ended December 31 last, the Vaal Reefs has been sampled to the extent of 1,285 ft., averaging 92.4 dwt. over 5.3 in., equivalent to 487 in. dwt., up to the end of February last. Of the total sampled 1,175 ft., equal to 91.4 per cent, proved payable and averaged 99.6 dwt. over 5.26 in., equivalent to 524 in. dwt.

Marlu Gold Pays 5 Per Cent

Marlu Gold Mining Areas, the West African gold producer, man Gold Mining Areas, the West African gold producer, in a preliminary profit statement has recommended the payment of 5 per cent per 5s. unit for the year ended September 30, 1953. This was the company's first distribution since 1940/41 when 10 per cent was paid.

Subject to completion of the audit, operating profits expanded from £48,011 to £124,551, and after providing for the 5 per cent dividend, which required £55,000, the carry forward was £125,799 compared with £57,425 brought in.

Marlu has maintained its all round improvement during the current year and at the end of the first six months the monthly production returns issued by the company reveal a cumulative profit to the end of March last of £80,700 compared with £79,200 in the corresponding period of the year under review.

Major Gen. W. W. Richards is chairman. The report and accounts will be posted towards the end of next week and the meeting has been provisionally arranged for May 6.

Good Diamond Sales in March Ouarter

The good diamond sales effected through the Central Selling Organization during the first three months ending March 31, 1954, amounting to £16,655,064, do not bear out Sir Ernest Oppenheimer's forecast in June, 1953, that boom times have come to an end.

Indeed, the industrial diamonds sold during the March quarter, 1954, were the highest achieved in any quarter since the three months ended September 30, 1952, when the sales of industrial stones totalled £5,353,927.

Sales of both gems and industrials effected through the C.S.O. during the past five quarters are shown below.

Quarter	Gems	Industrials	Totals
March, 1953	£14,507,190	£4,066,018	£18,573,208
June, 1953	£8,792,258	£4,084,716	£12,876,974
September, 1953	£9,303,346	£4,833,746	£14,137,092
December, 1953	£10,733,315	£4,835,352	£15,568,667
March. 1954	£11.773.849	£4.881.215	£16,655,064

Rhodesian Corporation Maintains Dividend on Lower Earnings

Rhodesian Corporation, in a preliminary profit statement, have recommended the payment of a final dividend of 5 per cent making, with the interim payment of $2\frac{1}{7}$ per cent, a total distribution for the year ended September 30, 1953, of $7\frac{1}{7}$ per cent, the same as was paid in the preceding year.

Year to Sept. 30	Working Profit	Taxa- tion	Net Profit	Divide Distribu		Carry Forward
	£	£	£	£	%	£
1953	26,860	1,592	25,268	39,722	74	29,102
1952	67,672	3,325	64,347	38,500	71	43,556


The dividend is payable to shareholders registered as at April 30 and warrants will be posted on June 10.

Mr. L. C. Walker is chairman. Meeting, London, June 10.

QUALIFIED YOUNG MEN, preferably single, required for training as Junior Engineers with a Mining Engineering Company specializing in high-speed fully mechanized tunnelling. Applicants should apply stating age, full details of education and qualifications, to Box No. 549, The Mining Journal, 15 Wilson Street, Moorgate, London, E.C.2.

OUT OF YOUR GROUND

There are so many occasions when one realises how difficult it is to be well-informed on all the financial problems which arise in these complicated days. That is why our organisation includes a number of departments



WESTMINSTER BANK LIMITED

THE ANGLO-FRENCH EXPLORATION COMPANY, LIMITED

The 64th Annual General Meeting of the Anglo-French Exploration Company Limited was held on April 2 in London.

The Chairman, Mr. F. R. Cottell, A.C.A., in the course of his speech said:—

Our investments stand in the books at £990,859 and are valued at £1,215,103, an excess of £224,244. The classification of our investments based on the valuation at December 31, 1953, is:—

Gold Mi	ning	(includ	ling 1	nolding o	comp	anies	
which	have	substa	ntial	interests	in	gold	
mining	com	panies)		***			63.0%
Oil							13.7%
Copper, 1	ead,	zinc					8.0%
Tin					***		8.0%
Coal							7.0%
Miscellan	eous				***		0.3%

In the profit and loss account it will be observed that our dividend income continues to rise and I would mention that the year's figure of £82,322 is the highest recorded since this item was first entered in our accounts at the gross amount, which was in 1941. This is particularly satisfactory in that we have substantial interests in gold mining companies on the Far West Rand and in the Orange Free State which either have not yet reached the dividend paying stage or have not attained full productive capacity. The prospective dividends from these interests should enable us at least to maintain our revenue from investments despite some probable falling off in the return from our base metal interests. The profit for the year, after taxation, is £33,320 against £31,938 in 1952. A dividend for the year of 7½ per cent is recommended.

Despite the hopes which were current last year that steps would be taken internationally to raise the dollar price of gold and to bring the paper currencies of all members of the International Monetary Fund more into line with their real value in terms of gold, it appears that the United States Authorities are still firmly disposed to ignore the fact that the paper dollar is worth only one-half of its pre-war value in terms of commodities. The inadequacy of world gold reserves in relation to the dollar value of international trade has been clearly demonstrated in a report prepared for the International Monetary Fund by Mr. Roy F. Harrod, entitled "Imbalance of International Payments." It follows, in order that full convertibility of currencies may be attained, that effective steps must eventually be taken to increase world gold reserves and this can only be done by raising the dollar price of gold. It is understood that representations in support of such action have been made to the United States Authorities by Mr. Butler, Chancellor of the Exchequer, while Mr. Havenga, South African Finance Minister, has been a consistent advocate of a higher world price for gold. We must continue to hope that too long a delay will not occur before this urgently needed step is taken.

By the end of 1953 23 gold mining companies in the Transvaal and the Orange Free State had entered into contracts with the Atomic Energy Board of South Africa for the sale of uranium. Stockholders will be interested to learn that the major proportion of this company's direct investment in South African developing or operating gold mines is in companies which are in this category of prospective uranium producers.

Apex Mines, Limited, had a successful year, achieving an increase in working profit and dividends declared. Operations at the properties of The Rooiberg Minerals Development Company, Limited, continued to expand and despite a fall in the average price realized for its tin concentrates in comparison with the previous year, the company was able to pay satisfactory dividends.

The net profit, after tax, of Apex (Trinidad) Oilfields, Limited, for the year ended September 30, 1953, was £584,206; the dividend was increased from 2s. 3d. tax free, per 5s. stock unit, to 2s. 6d. free of tax.

I regret that I am unable to report any satisfactory progress in the resumption of normal operations by Anglo-Burma Tin Company, Limited. Owing to the continuance of disturbed conditions in the company's area the output from the mine continues to be but a fraction of what could be achieved by full-scale working. There has been a suggestion by the Burma Government of a joint working arrangement with tin mining companies in Lower Burma but this matter is still in the very early exploratory stages.

The report and accounts were adopted.

ANGLO AMERICAN CORPORATION OF SOUTH AFRICA, LIMITED

(Incorporated in the Union of South Africa)

MINING COMPANIES' REPORTS (abridged) for year ended 31st December, 1953

(All companies mentioned are incorporated in the Union of South Africa)

BRAKPAN MINES LIMITED

Tons milled 1,377,000.	Yiel	d (per ton, 3.58 dwt.)24	16,290 oz.
theome and Expenditure	Account	Appropriation Accou	£
*Revenue (per ton milled		Union Government In-	
44/11.9)	3,097,922	come Tax	40,67
Working Costs (per ton		Provincial Tax	17
milled 40/4.1)	2,777,502	Government Share of Pro-	22.04
Wallan Barrett		fits under Mining Lease Dividends No. 81 of 6d.	23,84
Working Profit (per ton milled 4/7.8)	320,420	per share and No. 82 of	
Sundry Revenue less Ex-	320,420	6d. per share	230,00
penditure	77,209	Directors' Special Remun-	230,00
penditure	.,,20	eration	7.50
Total Profit	397,629	Appropriation for Capital	
Add-		Expenditure	47,82
Balance to credit of Ap-		Balance unappropriated at	
propriation Account		December 31, 1953	338,86
at December 31, 1952	186,529		
Silicosis Outstanding			
Liabilities Trust Fund -refund	4,738		
Amount previously Ap-	4,/36		
propriated for Stand-			
ard Stock now written			
back	100,000		
	£688,896		£688.89

Working revenue includes £45,697 in respect of the premium arising from the sales of gold at enhanced prices for industrial and artistic purposes.

ORE RESERVE (based on pay limit of 3.6 dwt.) (1952—3.4 dwt.):

Tons Stope Width Stope Value Inch-dwt. (inches)

1. 3,925,600 43.91 4.66 205

1. 3,547,600 44.76 4.66 209

The value of the ore mined from the Reserve in 1953 was 4.60 dwt. DEVELOPMENT:—

Average reef width (inches) 49.68 Average Footage Percentage ref width
Advanced Sampled Payable ref width
62,747 45,870 28.1 49.68 14.90
Included in the above development is footage accomplished on the footwall reef which totalled 11,884 feet, of which 8,705 feet was sampled, 42.8 per cent being payable, averaging 17.49 with over 94.2 inches care the footage and the footage accomplished on the footwall reef which totalled 11,884 feet, of which 8,705 feet was sampled, 42.8 per cent being payable, averaging 17.49 with over 94.22 inches care the footage and the footage accomplished on the footage accomplished accomplish

SPRINGS MINES LIMITED

CAPITAL: Authorised and Issued—£2,527,500 in 10,110,000 Shares of Ss. each, fully paid.

Tons willed 1 735 000	\$21.4	16	
Income and Expenditure	Account	Appropriation Accou	18,895 OZ
income and expenditure	Account	Appropriation Accou	int
*Revenue (per ton milled	L	History of the No.	2
Revenue (per ton inilied		Union Government Nor-	
34/7.5)	3,003,842	mal Tax	1,25
Working Costs (per ton		Provincial Tax	25
milled 32/10.1)	2,848,914		
	-	Profits under Mining	
Working Profit (per ton		Lease	9,22
milled 1/9.4)	154,928	Appropriated for Capital	
Sundry Revenue, less Ex-		Expenditure	2.06
penditure	4,792	Capital Issue Expenses	-,
	-	West Springs, Ltd., For-	
Total Profit	159,720	feited Dividends-Paid	
Add-		Dividend No. 63 of 11d.	
Balance to credit of Ap-		per share	63,18
propriation Account		Dividend No. 64 of 11d.	00,10
at December 31, 1952	317,566	per share	63.18
Outstanding Liabilities		Directors' Special Remun-	03,10
Trust Fund-refund.	1.808	eration	4,28
Amount previously ap-	1,000	Balance unappropriated at	4,40
propriated for Stand-		December 31, 1952	438 63
ard Stock now written		December 31, 1932	435,63
back	100.000		
Date	100,000		
	£579.094		£579.09

* Working revenue includes £42,824 in respect of the premium received in the sales of gold at enhanced prices.

ORE RESERVE (based on pay limit of 3.1 dwt.) (1952—2.9 dwt.):

Stope Width Stope Value Inch-dwt.

(inches) (dwt.)

3. 327,500 43,51 4,37 190
3. 2,764,100 43,51 4,61 201

1952. 3,327,500 43,51 4.37 190
1953. 2,764,100 43,51 4.61 201
The Reserve includes ore on the Kimberley Reef Series, which totalled 35,000 tons, averaging 3,15 dwt. over a width of 46,73 inches. The value of the ore mined from the Reserve in 1953 was 4,41 dwt.

DEVELOPMENT:—

Properties:—

DEVELOPMENT —

DEVELOPMENT — Footage Sampled

DEVELOPMENT:—
Footage Advanced Sampled payable reef width (inches)

27,717 23,740 35.7 16.23 30.52
Reference was made in last year's report to the fact that operations on the Kimberley Reef horizon were confined to stoping, and that tonnage from this source was on a diminishing scale. It is anticipated that all work on the Kimberley Reef will be completed during the current year.

DAGGAFONTEIN MINES. LIMITED

CAPITAL: Authorised-£2,000,000. Issued-£1,750,000 in 7,000.000 Share of 5s. each, fully paid.

Tons milled 2,609,500. Yield (per ton, 4.70 dwt.) 613,874 oz

Income and Expenditure	Account	Appropriation Acco	unt
	£		£
*Revenue (per ton milled		Union Government In-	
59/1.6)	7,715,034	come Tax	1,367,073
Working Costs (per ton		Provincial Tax	1,626
milled 28/6.2)	3,720,317	Government share of	
	***************************************	Profits under Mining	206 334
Working Profit (per ton		Lease	706,330
milled 30/7.4)	3,994,717		
Uranium and Sulphuric		Liability under Silicosis	£ 225
Acid Profit—subject to		Act, 1946	5,227
adjustment	644,991		400,000
Sundry Revenue less Ex-	00 100	Dividend No. 41 of 3s.	400,000
penditure	82,179	per share	1.050.000
T	4,721,887	Dividend No. 42 of 3s.	1,030,000
Total Profit	4,/21,00/	per share	1.050,000
Add— Balance to credit of Ap-		Directors' Special Remun-	1,000,000
propriation Account		eration	7,500
at December 31, 1952	311.685	Appropriation for Capital	.,
Amount previously ap-	211,000	Expenditure	65,105
propriated for Stand-		Balance unappropriattd at	
ard Stock now written		December 31, 1953	455,711
back	75,000		
District		-	
	£5,108,572		£5,108,57
			The same of the sa

*Working revenue includes £102,904 in respect of the premium arising from the sales of gold at enhanced prices.

ORE RESERVE (based on pay limit of 2.8 dwt.) (1952-2.6 dwt.) : Stope Width (inches) (dwt.) 44.29 5.73 43.83 5.48 Tons Inch-dwt.

The Reserve includes 5,362,100 tons, averaging 6,78 dwt, over a width of 48,31 inches on the Kimberley Reef series.

The value of the ore mined from the Reserve in 1953 was 5.95 dwt

DEVELOPMENT :-

	Foot	age	Percentage	Average	Average
	Advanced	Sampled	payable	reef width	assay value (dwt.)
Main Reef Leader	23,701	20,670	61.0	14.52	23.32

CAPITAL EXPENDITURE.—During 1953 the expenditure under this heading on shaft sinking, development and equipment totalled £61,159; it is estimated that an amount of £25,000 will be expended for the curreyear. These figures are exclusive of expenditure on the uranium and acid plants, which in the year under review amounted to £814,617 and the estimated expenditure for 1934 is £150,000.

URANIUM.—The construction of the uranium and acid plants was opened officially by Sir Ernest Oppenheimer on May 22, 1953.

By the end of 1953 the total expenditure on the uranium and acid plants, including interest payable under the loan agreements, amounted to £4,578,724. The final cost of the plants is now estimated to be about £4,425,000, excluding interest on the loans.

As the final cost of the uranium and acid plants is somewhat in excess of the loans made to the Company, application has been made for further borrowings during 1954 to meet the total cost. In order that the Directors of the Company may enter into supplementary loan agreements, it will be necessary for their borrowing powers to be increased beyond the £4,000,000 at present authorised. Shareholders will, therefore, be asked at an Extraordinary General Meeting to be held immediately after the Annual General Meeting to consider the passing of an Ordinary Resolution to increase the borrowing powers of the Directors from £4,000,000 to £4,750,000. This latter amount is considered to be sufficient to cover the total loan facilities required to finance the cost of the uranium and acid plants and to provide a margin for any temporary borrowings by the Company.

The estimated net profit of £644,991, derived from the production of uranium and acid is subject to adjustment and covers a period of nine months during which the plants were gradually being brought into full production. Such adjustments as are necessary will be brought into the accounts for 1954.

EAST DAGGAFONTEIN MINES. LIMITED

CAPITAL: Authorised—£2,000,000. Issued—£1,865,000 in 3,730,000 Shares of 10s. each, fully paid.

Tons milled 1.104,500.	Yiel	d (per ton, 3.46 dwt.)19	20,905 oz.
Income and Expenditure	Account	Appropriation Accou	mt £
*Revenue (per ton milled 43/5.7). Working Costs (per ton milled 32/2.3)	2,401,084 1,777,961	Union Government Income Tax	284,895 340
Working Profit (per ton milled 11/3.4)	623,123	1946 Dividend No. 27 of 9d.	4,158
Sundry Revenue, less Ex- penditure	4,327	per share Dividend No. 28 of 104d.	139,875
Total Profit	627,450	per share Directors' Special Remun- eration	8,000
Balance to credit of Ap- propriation Account at December 31, 1952	196,355	Appropriated for Capital Expenditure	2,610
Amount previously ap- propriated for Stand- ard Stock now written	170,333	December 31, 1953	270,739
back	50,000		
	£873,805	-	€873,805

* Working revenue includes £34,198 in respect of the premium arising from sales of gold at enhanced prices.

 ORE RESERVE (based on pay limit of 3.3 dwt.) (1952—3.2 dwt.):

 Tons
 Stope Width (inches)
 Stope Value (dwt.)
 Inch-dwt.

 2.
 4,360,300
 36.83
 4.43
 163

 3.
 4,332,400
 36.89
 4.35
 169
 1952 4,360,300 1953 4,332,400

The Reserve includes 1,261,000 tons averaging 5.48 dwt. over a width of 37.12 inches on the Kimberley Reef Series. The value of the ore mined from the Reserve in 1953 was 4.46 dwt.

DEVELOPMENT :-

in 1953 was 4.46 dwi.

INT:
Footage
Advanced Sampled
Advanced Sampled
24.2

Average Average reef width assay value (inches) (dwt.)
7.34
29.75
4.69
64.05 Main Reef Leader Kimberley Reef

THE SOUTH AFRICAN LAND AND **EXPLORATION COMPANY, LIMITED**

CAPITAL: Authorised—£500,003. Issued—£433,125 in 2.475,000 Shares of 3s. 6d. each, fully paid.

Tons milled 1,204,500.	Yiel	d (per ton-3.65 dwt.)2	19,850 oz.
Income and Expenditure	Account	Appropriation Accord	unt
*Revenue (per ton milled 45/10.1)	2,760,822 2,098,829	Union Government Tax Provincial Tax Government Share of Profits under Mining	275,191 452
Working Profit (per ton milled 10/11.9)	661,993	Increase in Terminal Liability under Silicosis	9
Sundry Revenue, less Ex- penditure	10,287	Act, 1946 Dividend No. 30 of 1s. 3d.	6,345
Total Profit	672,280	Dividend No. 31 of 1s. 6d.	154,687
Add— Balance to credit of Ap-		per share Directors' Special Remun-	185,625
propriation Account December 31, 1952	172,807	Appropriated for Capital	7,515
Amount previously ap- propriated for Capital		Expenditure Balance unappropriated at	31,255
Expenditure written back	75,000	December 31, 1953	259,008
	£920,087		£920,087

Working revenue includes £38,387 in respect of the premium arising from the sales of gold at enhanced prices.

ORE RESERVE (based on pay limit of 3.4 dwt.) (1952—3.2 dwt.):
Tons Stope Width Stope Value Inch-dwt. (dwt.)
1952. 3.424.300 42.22 5.01 212
1953. 3.198.200 441.60 5.22 217
The value of the ore mined from the Reserve in 1953 was 4.93 dwt. DEVELOPMENT :--Footage Advanced Sampled Average Pavable

Average reef width (inches) 25.21 assay val (dwt.) 19.13 39,930 32.2 59,958

CAPITAL EXPENDITURE:— During the year under review expenditure under this heading on shaft ting, development and equipment amounted to £28,561; expenditure the current year is estimated to be £20,000.

WESTERN REEFS EXPLORATION AND DEVELOPMENT COMPANY.

CAPITAL: Authorised—£2,000,000; Issued—£1,750,000 in 7,000,000 Shares of 5s. each, fully paid.

ccount	Appropriation Acco	Account	Income and Expenditure
£		£	
	Provincial Tax	3,359,136	Revenue (per ton milled 51/2.2)
sis	Increase in Terminal Li- ability under Silicosis	2,379,096	Working Costs (per ton milled 36/3.0)
6	Act, 1946		Working Profit (per ton
437	per share	980,040	milled 14/11.2) Uranium and Sulphuric
437	per share	20.000	Acid Profit-subject to
		246,645	adjustment
8	Transfer to Uranium Re-	14,563	Sundry Revenue, less Ex- penditure
	serve	14,505	penditure
at	Balance unappropriated at	1,241,248	Total Profit
382	December 31, 1953		Add— Funds previously appro- priated for Standard Stock now written
		100,000	Balance to credit of Ap-
		280,458	propriation Account at December 31, 1952
£1,621		£1,621,706	

* Working revenue includes £47,228 in respect of the premium arising from the sales of gold at enhanced prices.

 ORE RESERVE (based on pay limit of 3.2 dwt.) (1952—3.0 dwt.) :

 Tons
 Stope Width (inches) (finches)
 Stope Value (Inch-dwt.)
 Inch-dwt.

 2.
 4,703,000
 47.29
 5.03
 238

 3.
 4,763,000
 47.46
 4.88
 232

The Reserve includes 86,000 tons, averaging 14.76 dwt. over a width of 40.51 inches on the Vaal Reef horizon.

The value of the ore mined from the Reserve in 1953 was 5.41 dwt. DEVELOPMENT :-

HENT:—Gotage Footage Advanced Sampled as 83,153 42,700 51.1 Average reef width assay value (inches) (dwt.) 26.58 16.19 Mining Lease Area 83,153 42,700 51.1

Included in the above is footage accomplished on the Vaal Reef horizon, which totalled 17,261 feet, of which 2,815 feet were sampled, 2,565 feet (91.1 per cent.) being payable, averaging 100.89 dwt. over 8.90 inches, or 898 in.-dwt.

In addition to the above, prospecting development was accomplished in a portion of Farm Goedgenoeg No. 62, which is outside the Mining Lease Area, but over which your Company holds rights under the Reserved Minerals Development Act. The footage advanced in this area totalled 7,225 feet, of which 3,751 feet were on reef and 3,755 feet sampled; the payable footage amounted to 1,405 feet (37.4 per cent), averaging 11.91 dwt. over 40.42 inches, or 481 in.-dwt.

CAPITAL EXPENDITURE.—During 1953 the expenditure under this heading on shaft sinking, development and equipment totalled £424,958, of which £209,959 was incurred in connection with the No. 3 Vertical Shaft; it is estimated that an amount of £75,000 will be expended for the current year. These figures are exclusive of expenditure on the uranium and acid plants, which in the year under review amounted to £1,645,392, and the estimated expenditure for 1954 is £250,000.

URANIUM.—The construction of the uranium and acid plants proceeded satisfactorily and the official opening of the uranium plant was performed by Dr. A. J. R. van Rhijn, Minister of Mines, on December 4, 1953.

By the end of the year under review the total expenditure on the uranium and acid plants, including interest payable under the loan agreements, amounted to £5,320,636. The final cost of the plants is now estimated at about £5,290,000, excluding interest on the loans.

The estimated final cost of the uranium and acid plants is in excess of the loans so far made to the Company and application has been made for further borrowings during 1954 to cover the additional funds required.

The estimated net profit of £246,645 derived from the production of uranium and acid is subject to adjustment and covers a period of just over three months during which the uranium plant was being brought into full production. Such adjustments as a renecessary will be brought into the accounts for 1954.

LOANS—NATIONAL FINANCE CORPORATION OF SOUTH AFRICA.—During the year the Company entered into an agreement with the National Finance Corporation of South Africa, in terms of which the Finance Corporation advanced the Company the sum of £500,000 against the issue of Unsecured Redemable Debentures. The repayment of the Debentures has been guaranteed by the Anglo American Corporation of South Africa, Limited.

ORKNEY TOWNSHIP.—The Company is the owner of Orkney Township. During the year 8 stands were sold for £725 and a balance of 1,218 stands are still available for sale. Total collections in respect of sales of stands since the inception of the Township had amounted to £90,424 at the end of 1953.

SHAREHOLDINGS.—The Company disposed of its holding of 6,392 res in Vaal Reefs Exploration and Mining Company, Limited, during

VAAL REEFS EXPLORATION AND MINING COMPANY, LIMITED

EXTRACT FROM THE STATEMENT BY THE CHAIRMAN, MR. R. B. HAGART, CIRCULATED WITH THE ANNUAL REPORT AND ACCOUNTS FOR THE YEAR ENDED DECEMBER 31, 1953.

During the year under review work continued on the opening up and proving of the Company's property, with satisfactory results.

The No. 3 vertical shaft system of Western Reefs Exploration and Development Company, Limited, in which your Company has a joint interest, is now fully equipped and working normally, and the equipment of the sub-vertical shaft is nearly complete. Twin haulages have been driven on the 4,000 foot level from the joint shaft to the site of your Company's projected No. 1 Shaft system and preparatory work is in progress for the simultaneous sinking of the No. 1 vertical and sub-vertical twin shafts.

Development was commenced from the Western Reefs No. 3 sub-vertical shaft, and, as revealed in the report of the Consulting Engineers, 8,116 feet was accomplished, 823 feet of which was on Vaal Reef. The footage sampled was 810 feet, giving 92 per cent payable averaging 99.43 dwt. over 5.54 inches, or 551 in.-dwt.

In view of these values and those obtained on the Vaal Reef horizon in the adjoining property of Western Reefs Exploration and Development Company. Limited, together with the evidence, provided by surface boreholes, of the existence of Vaal Reef over the whole of the Company's prospecting lease area, a formal application has been made to the Mining Leases Board for a mining lease over the area concerned, comprising 6,918 claims; and, subject to the raising of additional capital referred to later, the mine will be equipped for crushing as soon as possible.

The crushing plant is to be equipped to crush 65,000 tons per month,

to be increased later to 75,000 tons and, having regard to the work already accomplished, it is hoped that the crushing of development rock will commence at the beginning of 1956 and the milling of stoping ore before the end of that year.

The additional capital which will be required to carry these plans to completion and to repay the present temporary loan of approximately £600,000 is estimated at approximately £8,000,000, of which about £2,400,000 will be spent on capital account during 1954. The Directors consider that about £3,500,000 of this money should be raised immediately by means of an issue of further shares.

will be spent on capital account during 1994. The Directors consider that about \$4.500,000 of this money should be raised immediately by means of an issue of further shares.

Further particulars regarding the raising of additional capital were circulated to shareholders on March 9, 1954, and an Extraordinary General Meeting of shareholders has been convened for March 31, 1954, to consider increasing the authorised capital of the Company to provide the reserve shares necessary to proceed with the proposed issue.

The Consulting Engineers consider that the uranium values disclosed in underground development and in boreholes sunk from the surface justify your Company's applying to become a uranium producer, and application has accordingly been made to the Atomic Energy Board. If this application is granted, the funds necessary for the uranium production plant will be raised by means of loans, so that there will be no need to call on shareholders to provide any finance for this purpose. The Extraordinary General Meeting already mentioned will also be asked to increase the maximum amount which the Directors are authorised to borrow from £1,500,000 to £5,000,000, a sum which will be sufficient to cover the loans needed in connection with uranium production, and to leave a margin for any temporary borrowing that may be necessary for any other purpose.

(1) Owing to fluctuations in the dollar sterling exchange rate, the official price of gold sold during the year varied between 246s. 8d. and 248s. per fine ounce.

THE FULL REPORTS AND ACCOUNTS CAN BE OBTAINED FROM THE LONDON SECRETARIES OF THE COMPANIES, ANGLO AMERICAN CORPORATION OF SOUTH AFRICA LIMITED, II, OLD JEWRY, LONDON, E.C.2.

CENTRAL MINING-RAND MINES GROUP

NOTICE IS HEREBY GIVEN THAT THE ORDINARY GENERAL MEETINGS OF THE UNDERMENTIONED COMPANIES WILL BE HELD IN THE BOARD ROOM, SECOND FLOOR, THE CORNER HOUSE, COMMISSIONER STREET, JOHANNESBURG, AS FOLLOWS:

Name of Company (each incorporated in the Union of South Africa)	Date of Meeting	Time	Transfer Books and Registers of Members close as under (both days inclusive) 1954
Crown Mines Limited	Monday 10th May	11 a.m.	4th to 10th May
East Rand Proprietary Mines, Limited City Deep Limited Transvaal Consolidated Land	do. do.	Noon 2.30 p.m.	do. do.
and Exploration Company Limited	do.	3.30 p.m.	do.
Limited	Tuesday 11th May	11 a.m.	5th to 11th May
Limited Rose Deep Limited Geldenhuis Deep Limited Rand Mines Limited	do. do. do. Friday 14th May	Noon 2.30 p.m. 3.30 p.m.	do. do. do. 8th to 14th May

ABRIDGED NOTICES OF "SPECIAL BUSINESS" TO BE CONSIDERED AT THE ORDINARY GENERAL MEETINGS OF

MODDERFONTEIN B. GOLD MINES LIMITED AND ROSE DEEP LIMITED

REDUCTION OF CAPITAL

MODDERFONTEIN B. GOLD MINES LIMITED

NOTICE IS ALSO HEREBY GIVEN that at the Ordinary General Meeting of MODDERFONTEIN B. GOLD MINES LIMITED shareholders will be asked to consider a resolution as a special resolution in terms of the Companies Act (1926), as amended, of the Union of South Africa, to allow for the reduction of the authorized capital of the Company from £350,000 to \$7280,000 by returning to shareholders paid-up capital which is £280,000 by returning to shareholders paid-up capital which is in excess of the wants of the Company to the extent of 6d. per share, thus reducing the nominal value of the shares from 2s. 6d. to 2s. each.

ROSE DEEP LIMITED

AND NOTICE IS ALSO HEREBY GIVEN that at the Ordinary General Meeting of ROSE DEEP LIMITED shareholders will be asked to consider a resolution as a Special Resolution in terms of the Companies Act (1926), as amended, of the Union of South Africa, to allow for the reduction of the authorized capital of the Company from £665,000 to £595,000 by returning to shareholders paid-up capital which is in excess of the wants of the Company to the extent of 2s. per share, thus reducing the nominal value of the shares from 19s. to 17s.

The Directors of the two above-mentioned Companies, in

continuance of the policy of making annual repayments of capital in preference to the declaration of dividends, recommends a further capital repayment which is considered to be the more appropriate form of distribution at this late stage in the life of the mines concerned.

GENERAL NOTE

In terms of the Companies Act, as amended, of the Union of South Africa, a member entitled to attend and vote at a meeting may appoint a proxy, or where allowed, one or more proxies to attend and vote on a poll and speak in his stead. A proxy need not be a member of the Company.

Those holders of Share Warrants who wish and have the right to be represented at these meetings, can obtain the necessary information regarding the formalities to be complied with and forms of proxy on application.

BY ORDER OF THE BOARDS, A. MOIR AND CO., London Secretaries.

Office of the London Secretaries: 4 London Wall Buildings, E.C.2. April 9, 1954.

SURVEYOR required for gold dredging company in British Guiana. Qualifications: A.R.S.M., A.C.S.M or equivalent. Experience of alluvial mine surveying, prospecting of alluvials and calculation of ore reserves desirable. Salary £750-£1,250 per annum, depending on qualifications and experience, plus overseas allowance £250, marriage allowance £100. Free furnished quarters required. Two ways town with four prooffsel case and provided. Two year tour with four months' leave and free passages. Apply in writing to Personnel, Colonial Development Corporation, 33 Hill Street, London, W.I., stating age, qualifications and experience and quoting Ser. No. 199.

NATIONAL COAL BOARD invite applications for two superannuable appointments as WORK STUDY EN-GINEER in their Production Department at London Headquarters. Candidates should have professional engineering qualifications, preferably in coal mining engineering (1st Class Certificate) although mechanical, electrical, and metalliferous mining engineers will be considered. Experience of work study though not essential is very desirable, but training will be given to otherwise suitable candidates lacking this experience.

The duties include assisting in the introduction of work study technique at collieries, and some lecturing, and will involve a certain amount of travelling.

Salary on appointment will be, according to qualifica-tions and experience, within a range £1,000-£1,450 inclusive, per annum.

Write, giving full particulars (in chronological order) of age, education, qualifications and experience (with dates) to National Coal Board, Establishments (Personnel), Hobart House, Grosvenor Place, London, S.W.I. marking envelope TT/766. Original testimonials should NOT be forwarded. Closing date April 30, 1954.

Metal and Mineral Trades

Established 1797

Members of the London Metal Exchange

DERBY & CO., LTD.

11-12 ST. SWITHIN'S LANE, E.C.4.

Telephone: MINCING LANE 5272

Specialists in

WOLFRAM, SCHEELITE, CHROME, MOLYBDENITE, TANTALITE, COLUMBITE RUTILE, ILMENITE, BERYL, ZIRCON AND OTHER MINERALS

Smelters and Refiners of

GOLD, SILVER, PLATINUM, PALLADIUM, OSMIUM, IRIDIUM, ETC.

Buyers of

MINERALS, ORES, CONCENTRATES, SWEEPS, LEMELS AND RESIDUES containing GOLD, SILVER, PLATINUM, COPPER, TIN, ZINC, LEAD

Also at:

NEW YORK :: ADELAIDE JOHANNESBURG SALISBURY (Rhodesia)

Smelting and Refining Works:

BRIMSDOWN, MIDDLESEX

LEONARD COHEN LTD.

GOLD, SILVER AND THE PLATINUM METALS ORES. CONCENTRATES AND RESIDUES METAL HARDENERS NON-FERROUS METAL INGOTS

London Office :

I HAY HILL, W.I Telephone : GROSVENOR 6284 Works:

PORTH, GLAM Telephone : PORTH 280 ROURA & FORGAS, LTD.

Telephone No: GERRARD 9641

Sole Sterling Area Suppliers of

AN QUICKSILVER

COLQUHOUN HOUSE. 27/37 BROADWICK STREET, LONDON, W.1

EASTERN SMELTING CO. LTD.

CAPITAL—AUTHORISED £500,000: £435,000 ISSUED

Head Office: ST. SWITHIN'S HOUSE, 11/12 ST. SWITHIN'S LANE, LONDON, E.C.4 Telegrams: TIMAMASA, PHONE LONDON

Telephone: MANsion House 2164/7

TIN SMELTERS

BRANCHES THROUGHOUT THE FEDERATION OF MALAYA

Sole Selling Agents: VIVIAN, YOUNGER & BOND, LIMITED, PRINCES HOUSE, 95 GRESHAM STREET, LONDON. E.C.2

Telephone: MONarch 7221/7

we buy CONCENTRATES ORES RESIDUES

containing

Base and Precious METAIS E. M. JACOB & CO. LTD.

Members of the London Metal Exchange

GREENWICH HOUSE, 10-13 NEWGATE ST., LONDON, E.C.1

Telephone: CITy 8401 (7 lines) Cables: JACOMETA, LONDON

Smee's 352/

ROKKER & STANTON LTD.

DRAYTON HOUSE, GORDON STREET LONDON, W.C.I

Metal Stockists & Shippers

BRASS, COPPER, ALUMINIUM AND NICKEL SILVER

Sheets, Rods, Tubes, Strip, Wire, etc.

Associated Companies in Holland and Belgium; also Regd. in South Africa and Rhodesia

Tel: EUS 4751/2 Cables: BENTLY 2nd; A.B.C.6 Grams: ROKKER, WESTCENT, LONDON

MINING & CHEMICAL PRODUCTS, LTD.

86, STRAND, W.C.2

Telephone: Temple Bar 6511/3 Works: ALPERTON Telegrams: "MINCHEPRO, LONDON" WEMBLEY, MIDDLESEX

Buyers of Silver Ores and Concentrates

Smelters and Refiners of

BISMUTH

ORES, RESIDUES & METAL

Manufacturers of:

FUSIBLE ALLOYS, SOLDER, WHITE METALS, ANODES OF TIN, CADMIUM and ZINC IN ALL SHAPES

Importers and Distributors of:

ARSENIC . BISMUTH . CADMIUM INDIUM . SELENIUM . TELLURIUM

PLATT METALS

METAL MANUFACTURERS and MERCHANTS

BRASS ROD SWARF AND SCRAP, and all descriptions of NON-FERROUS SCRAP METALS, BORINGS AND RESIDUES

Sellers of BILLETS AND INGOTS TO ANY REQUIRED COM-POSITION, GRADED NON-FERROUS SCRAP METALS

METALEX WORKS, Great Cambridge Road, ENFIELD, Mddx.

Telephone: HOWard 3351 (5 lines)

Telegrams: Walton, Enfield

THE STRAITS TRADING

Head Office:

P.O. Box 700, OCEAN BUILDING, SINGAPORE

Works :

SINGAPORE & PENANG

"The Straits Trading Co., Ltd." **Brand of Straits Tin**

GEORGE T. HOLLOWAY CO. LTD.

Metallurgists & Assayers

ORE TESTING, WORKS AND METALLURGICAL RESEARCH LABORATORIES

Atlas Road, Victoria Road, Acton, LONDON, N.W.10

Telephone: ELGAR 5202

Grams and Cables: **NEOLITHIC LONDON**

THE BRITISH TIN SMELTING

COMPANY, LIMITED

Works: LITHERLAND, LIVERPOOL Smelters of Non-ferrous Residues and Scrap

London Agents:

W. E. MOULSDALE & CO., LTD.

2 Chantrey House, Eccleston Street, London, S.W.I Telephone: SLOane 7288/9 Cables: Wemoulanco, London

ZINC SHAVINGS

GRANULATED & POWDERED NON-FERROUS METALS

> "Lead Wool" for Pipe-jointing. Metallic Packing for Pumps, etc.

THE LEAD WOOL CO., LTD. SNODLAND

Telephone: Snodland 84216 & 7 Telegrams: "Strength, Phone, Snodland "

MAYBANK METALS LTD.

This Company backed with the vast experience gained in a 100 YEARS of progressive trading, will expedite all orders . . .

THE BUYING OF MIXED OR SORTED NON-FERROUS SCRAP METALS and Supplying of Finely Graded Non-Ferrous Scrap to Your Requirements.

AYBANK METALS LTD.

STAR WORKS, SPURGEON STREET, SOUTHWARK LONDON, S.E.I Telephone: HOP 2432/3 HOP 4212/3/4

H. BARNETT LTD.

VICTOR ROAD, LONDON, N.7. IMPORT : EXPORT

Phone: ARCHWAY 5461 (5 lines) WE SPECIALISE IN ALL NON-FERROUS SCRAP AND INGOT METALS

CUPELS

MAGNESIA CUPELS and ASSAY MATERIAL "MABOR" BRAND, as supplied to MINTS, MINES and ASSAYERS throughout the World.

MABOR (1944) LIMITED (Founded 1900)

THE PIONEERS OF MAGNESIA CUPELS

Registered Office: 310 Winchester House, London, E.C.2 Phone: London Wall 5089 Tel. Address: Maborlim, London Agencies: SALEM, INDIA: MONTREAL, CANADA: PERTH, W.A.

Supplies through Agents, the Trade, or direct.

TINPLATES - BLACKPLATES

Strips, Circles, Printers' Waste

EXPORT & HOME MARKET

Prompt attention to all enquiries

BAYSWATER METAL SUPPLY CO. 8, LADBROKE WALK,

LONDON, W.II. ENGLAND

Phone: BAY 7541

Cables: ALMETSUP, LONDON

International Smelters and Buyers of

NON-FERROUS SCRAP METALS A RESIDUES

LEAD WHITEMETAL SOLDER GUNMETAL COPPER

THE EYRE SMELTING CO LTD

Tandem Works, Merton Abbey, London, S.W.19

Phone: Mitcham 2031

Wire: Eyrsmeltin, Phone, London

EVERITT & Co. LTD.

40 CHAPEL STREET LIVERPOOL

Teleg. Address: Persistent, Liverpool

Phone: 2995 Central

SPECIALITY

MANGANESE PEROXIDE ORES.

We are buyers of :-WOLFRAM, SCHEELITE, MOLYBDENITE VANADIUM, ILMENITE, RUTILE, ZIRCONIUM and TANTALITE ORES

Suppliers of :-FERRO-ALLOYS & METALS NON-FERROUS ALLOYS

CHARLES KERRIDGE

SCRAP LEAD
 BATTERY PLATES
 NON-FERROUS CONTENTS

FENCEPIECE ROAD, CHIGWELL, ESSEX

Telephones: Hainault 2903, Larkswood 3863

Telegrams: Metallia East Phone London

Transit

Tropag

ASBEST-& ERZIMPORT OSCAR H. RITTER K. G. Ballindamm 7 Hamburg

ASBESTOS - ORES - MINERALS

Import Export

ENTORES. LIMITER

KINGS HOUSE, 36 & 37 KING STREET, LONDON, E.C.2

NON-FERROUS METALS ORES · RESIDUES

Telegrams: Entores, Phone, London

Telephone: MONarch 3415

We are Buyers of.

Monazite . Beryl Ore Lithium Ores . Tantalite **Selenium Containing Materials**

Please send vour detailed offers to:-

NEW METALS & CHEMICALS (Sales) Ltd.,

16 NORTHUMBERLAND AVENUE, LONDON, W.C.2.

Telephone: WHItehall 0573 (5 lines) Cables: "Newmet London" International Telex: London 8016

Warehouses at: CRAVEN HOUSE, CRAVEN STREET, W.C.2 and LONDON BRIDGE STREET, S.E.1

RICHMOND'S SOUTH AFRICAN ALL MINING YEAR BOOK 1953

accompanied by

SPECIAL MAP OF THE UNION OF SOUTH AFRICA AND SOUTH-WEST AFRICA

on two sheets, combined size 40 in. x 52 in., illustrating the location of every MINE, QUARRY and WORKS

The Union of South Africa and South-West Africa has a regular production of over 70 Metals and Minerals.

There are over 700 Mining Companies, Syndicates or Operators on more than 800 Mines, Quarries and Works, including 125 Gold Mines, 59 Collieries, 17 Diamond Mines, 15 Chrome Mines, 98 Asbestos Mines, 49 Limestone and Dolomite Quarries, etc., etc.


Richmond's South African All Mining Year Book will give you, in carefully indexed form, useful, up-to-date information on all Metals and Minerals, Producers, Operators and Properties.

A Unique Addition to the Book is a two sheet Map of the Union of South Africa and South-West Africa on which is plotted the position of every mine, quarry and works. A simple but effective index system enables you to refer from book to map and vice versa in the minimum of time.

Publishers: The Technical Map Service, Johannesburg

Obtainable in London from

The Mining Journal Price £3 3s. 0d. (plus 8d. postage)



WORLD-WIDE

DANIEL C.

BRISTOL BIRMINGHAM GLASGOW HULL LIVERPOOL NEWCASTLE

S. WALES

Technical representatives in sales of Ores & Metals at all Ports and Works.

Analyses of PRECIOUS METALS BASE METALS **ORES & RESIDUES**

Etc.

Telegraphic Address: "GRYFFYDD, LONDON."

SPAIN SWEDEN

SWITZERLAND

Telephones: HOP 1071 (2 lines) CANONBURY 5956

MONARCH 1314 (3 lines)

Cables & Telegrams: LUNZMETAL, LONDON

S. B. LUNZER & CO., LTD. Members of The National Association of Non-Ferrous Scrap Metal Merchants IMPORTERS NON-FERROUS METALS : SEMIS EXPORTERS

Office:—WESTMINSTER BANK CHAMBERS, LONDON BRIDGE LONDON S.E.I Warehouse:—16b ST. PAUL'S PLACE, CANONBURY, N.I.

HENEAGE METALS LTD. HENEAGE ST. BIRMINGHAM.

DEERING PRODUCTS LTD. 8 GREAT SMITH STREET, LONDON, S.W.I

ORES - MINERALS - REFRACTORY RAW MATERIALS

Telephone: ABBEY 2681/2

Cables: PRODEERING, LONDON



AGENTS IN MOST COUNTRIES THROUGHOUT THE WORLD



RAPID MAGNETIC MACHINES LIMITED
LOMBARD STREET, BIRMINGHAM, 12 Tel: VIC. 1137. 'Grams: "Magnetism, B'ham."



PT50a.